

LNPT[™] STAT-LOY[™] COMPOUND 63000CT

DESCRIPTION

LNP STAT-LOY 63000CT compound is based on Polycarbonate / Polyester alloy containing proprietary additives targeted for advanced semiconductor packaging applications. Added features of this grade include: LNP Clean Compounding Technology, Permanently Anti-Static, Translucent.

GENERAL INFORMATION

Features	Antistatic, Transparent/Translucent, Low ionics/Outgassing/Liquid particle count, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polycarbonate + Polyester (PC+Polyester)
Processing Techniques	Injection Molding

INDUSTRY

Electrical and Electronics
Industrial

SUB INDUSTRY

Electronic Components, Mobile Phone - Computer - Tablets
Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	35	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	200	%	ASTM D638
Tensile Modulus, 5 mm/min	1160	MPa	ASTM D638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	50	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1160	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	34	MPa	ISO 527
Tensile Strain, break, 5 mm/min	140	%	ISO 527
Tensile Modulus, 1 mm/min	1180	MPa	ISO 527
Flexural Modulus, 2 mm/min	1140	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	580	J/m	ASTM D256
Charpy Impact, notched, 23°C	69	kJ/m ²	ISO 179/2C
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 6.4 mm, unannealed	83	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	73	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	68	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.16	g/cm ³	ASTM D792
Mold Shrinkage, flow ⁽²⁾	0.6	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	16	g/10 min	ASTM D1238
Moisture Absorption (23°C / 50% RH)	0.7	%	ISO 62

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
OPTICAL ⁽¹⁾			
Light Transmission, 2.54 mm	81	%	ASTM D1003
Haze, 2.54 mm	10	%	ASTM D1003
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽³⁾	1.E+11 – 5.E+12	Ω	ASTM D257
Volume Resistivity ⁽³⁾	1.E+11 – 5.E+12	Ω.cm	ASTM D257
Static Decay, 5000V to <50V	<2	Seconds	FTMS101B
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	90 – 95	°C	
Drying Time	6 – 8	Hrs	
Melt Temperature	230 – 250	°C	
Nozzle Temperature	230 – 250	°C	
Front - Zone 3 Temperature	230 – 250	°C	
Middle - Zone 2 Temperature	225 – 240	°C	
Rear - Zone 1 Temperature	220 – 230	°C	
Mold Temperature	40 – 50	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Measurement meets requirements as specified in ASTM D4496.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.