



LNPT[™] THERMOCOMP[™] AM COMPOUND ZC004XXAR1

DESCRIPTION

LNP THERMOCOMP ZC004XXAR1 compound is based on Polyphenylene Ether / Polystyrene (PPE/PS) blend containing 20% carbon fiber for Large Format Additive Manufacturing (LFAM) applications. Added features of this grade include: Higher Stiffness vs. glass fiber, Lower Thermal Expansion, Improved Hydrolytic Stability, Higher strength to Weight Ratio, Higher Temperature Performance and improved processing vs. ABS based grades.

TYPICAL PROPERTY VALUES

Revision 20240209

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, 5mm/min ⁽¹⁾			
XZ Orientation	75	MPa	ASTM D638 Modified
ZX Orientation	21	MPa	ASTM D638 Modified
Tensile Strain, 5mm/min			
XZ Orientation	0.7	%	ASTM D638 Modified
ZX Orientation	1.0	%	ASTM D638 Modified
Tensile Stiffness, 5mm/min			
XZ Orientation ⁽²⁾	12.2	GPa	ASTM D638 Modified
ZX Orientation	2.7	GPa	ASTM D638 Modified
Flexural Stress, 5mm/min			
XZ Orientation	36	MPa	ASTM D790 Modified
ZX Orientation	99	MPa	ASTM D790 Modified
THERMAL			
HDT, 1.82 MPa, 3.2mm, annealed	137	°C	ASTM D648
PHYSICAL			
Specific Gravity	1.17	-	ASTM D792
EXTRUSION			
Extruder L/D	24	-	
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Barrel - Zone 1 Temperature	270 – 305	°C	
Barrel - Zone 2 Temperature	280 – 320	°C	
Barrel - Zone 3 Temperature	280 – 320	°C	
Barrel - Zone 4 Temperature	280 – 320	°C	
Nozzle Temperature	280 – 320	°C	
Melt Temperature	270 – 315	°C	
Bed Temperature	100 – 120	°C	
Extruder Pressure	<13.5	MPa	



- (1) Modified ASTM E8 used for tensile test samples
(2) Tensile Stiffness (K) is structural property defined as the stress/strain in the linear region of the stress-strain curve. Value depends on the geometry/shape and boundary/surrounding conditions

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.