

LNPTM THERMOCOMPTM COMPOUND 9X02540

PDX-02540

DESCRIPTION

LNP THERMOCOMP 9X02540 compound is based on Polycarbonate / Polyester blend containing 20% glass fiber. Added features of this grade include: Flame Retardant, Improved Impact.

GENERAL INFORMATION

Features	Flame Retardant, High stiffness/Strength, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polycarbonate + PET (PC+PET)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	108	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	108	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2.1	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.1	%	ASTM D638
Tensile Modulus, 50 mm/min	7650	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	149	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	153	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7030	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	103	MPa	ISO 527
Tensile Stress, break, 5 mm/min	103	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.1	%	ISO 527
Tensile Strain, break, 5 mm/min	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	7240	MPa	ISO 527
Flexural Stress	149	MPa	ISO 178
Flexural Modulus, 2 mm/min	6530	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	558	J/m	ASTM D4812
Izod Impact, notched, 23°C	51	J/m	ASTM D256
Multiaxial Impact	1	J	ISO 6603
Instrumented Dart Impact Total Energy, 23°C	13	J	ASTM D3763

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*4 +23°C	38	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	130	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	122	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	133	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	120	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	75	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.47	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.1	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽³⁾	0.1 – 0.4	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	0.3 – 0.5	%	ASTM D955
Moisture Absorption (23°C / 50% RH)	0.14	%	ISO 62
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-101284697	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.