

LNPT[™] THERMOCOMP[™] COMPOUND 9X22141

DESCRIPTION

LNP THERMOCOMP 9X22141 compound (also known as ER016141) is based on Polycarbonate (PC) and Acrylonitrile butadiene styrene (ABS) resins containing 20% glass fiber. Added features of this grade include: High Stiffness, Excellent Processing, Good Dimensional Stability, Good Impact Performance, UL94 HB Rating

GENERAL INFORMATION

Features	Good Processability, Dimensional stability, High stiffness/Strength, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polycarbonate + ABS (PC+ABS)
Processing Techniques	Injection Molding

INDUSTRY

Automotive

SUB INDUSTRY

Automotive EV

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Modulus, 1 mm/min	7000	MPa	ISO 527
Tensile Stress, break, 5 mm/min	114	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.7	%	ISO 527
Flexural Modulus, 2 mm/min	6200	MPa	ISO 178
Flexural Stress, yield, 2 mm/min	166	MPa	ISO 178
Flexural Stress, break, 2 mm/min	165	MPa	ISO 178
Tensile Modulus, 5 mm/min	7000	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	116	MPa	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	6600	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	172	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	169	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80°10°4 +23°C	11	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 0°C	11	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80°10°4 +23°C	63	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	12	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10°4 sp=62mm	52	kJ/m ²	ISO 179/1eU
Charpy 0°C, V-notch Edgew 80°10°4 sp=62mm	10	kJ/m ²	ISO 179/1eA
Izod Impact, notched, 23°C	110	J/m	ASTM D256
Izod Impact, notched, 0°C	110	J/m	ASTM D256
Izod Impact, unnotched, 23°C	700	J/m	ASTM D4812
Instrumented Dart Impact Energy @ peak, 23°C	18	J	ASTM D3763
THERMAL ⁽¹⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Elec	60	°C	UL 746B
Relative Temp Index, Mech w/impact	60	°C	UL 746B
Relative Temp Index, Mech w/o impact	60	°C	UL 746B
Vicat Softening Temp, Rate B/50	136	°C	ISO 306
Vicat Softening Temp, Rate B/120	138	°C	ISO 306
CTE, -30°C to 80°C, flow	3.8E-5	1/°C	ISO 11359-2
CTE, -30°C to 80°C, xflow	5.8E-5	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	132	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	137	°C	ISO 75/Bf
HDT, 1.82 MPa, 3.2mm, unannealed	132	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	136	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.29	g/cm ³	ISO 1183
Melt Flow Rate, 260°C/2.16 kgf	5	g/10 min	ASTM D1238
Melt Flow Rate, 260°C/5.0 kgf	20	g/10 min	ASTM D1238
Mold Shrinkage, flow ⁽²⁾	0.2 – 0.4	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.3 – 0.5	%	SABIC method
FLAME CHARACTERISTICS ⁽³⁾			
UL Yellow Card Link	E121562-104627828	-	-
UL Recognized, 94HB Flame Class Rating	≥0.75	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80 – 100	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 290	°C	
Rear - Zone 1 Temperature	250 – 280	°C	
Middle - Zone 2 Temperature	255 – 285	°C	
Front - Zone 3 Temperature	260 – 290	°C	
Nozzle Temperature	260 – 290	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.2 – 0.7	MPa	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.