

LNPT[™] THERMOCOMP[™] COMPOUND DF002FV

DESCRIPTION

LNP THERMOCOMP DF002FV compound is based on Polycarbonate (PC) resin containing 10% glass fiber. Added features of this grade include: Improved Plating Surface and Mechanical Performance targeted for Laser Direct Structuring (LDS) applications, Good Surface Aesthetics and Wide Processing Window.

GENERAL INFORMATION

Features	Dielectrics, Laser Direct Structuring, Aesthetics/Visual effects, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Automotive Interiors
Personal Accessory
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	60	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4.1	%	ASTM D638
Tensile Modulus, 5 mm/min	3800	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	110	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3600	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	700	J/m	ASTM D4812
Izod Impact, notched, 23°C	170	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm	125	°C	ASTM D648
HDT, 1.82 MPa, 3.2 mm	119	°C	ASTM D648
Relative Temp Index, Elec ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	80	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.27	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.3	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽³⁾	0.5	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	29	g/10 min	ASTM D1238

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
ELECTRICAL ⁽¹⁾			
Dielectric Constant, 1.1 GHz	3.05	-	SABIC method
Dielectric Constant, 1.9 GHz	3.05	-	SABIC method
Dielectric Constant, 5 GHz	3.03	-	SABIC method
Dissipation Factor, 1.1 GHz	0.014	-	SABIC method
Dissipation Factor, 1.9 GHz	0.013	-	SABIC method
Dissipation Factor, 5 GHz	0.011	-	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-102822332	-	-
UL Recognized, 94HB Flame Class Rating	0.5	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	110	°C	
Drying Time	3 – 4	Hrs	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	270 – 295	°C	
Front - Zone 3 Temperature	270 – 295	°C	
Middle - Zone 2 Temperature	270 – 295	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	100 – 120	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.