

LNPTTM THERMOCOMPTM COMPOUND FX10009

FX10009

DESCRIPTION

LNP THERMOCOMP FX10009 compound is based on Polyethylene (PE) resin containing proprietary fillers. Added features of this grade include: Improved Dielectric Properties.

GENERAL INFORMATION

Features	Dielectrics
Fillers	Unreinforced
Polymer Types	Polyethylene, Unspecified (PE, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Automotive Interiors
Personal Accessory
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	20	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.2	%	ISO 527
Tensile Modulus, 1 mm/min	2550	MPa	ISO 527
Flexural Stress, break, 2 mm/min	15	MPa	ISO 178
Flexural Modulus, 2 mm/min	2750	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	5.5	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3.5	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	1.30E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.50E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	100	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	60	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Melt Volume Rate, MVR at 190°C/10.0 kg	7.5	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 220°C/10.0 kg	12.5	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow ⁽²⁾	1.5 – 2.0	%	SABIC method
Density	2.50	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.08	%	ISO 62-1
ELECTRICAL ⁽¹⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dissipation Factor, 1 GHz	0.008	-	IEC 60250
Dissipation Factor, 500 MHz	0.008	-	IEC 60250
Dissipation Factor, 100 MHz	0.009	-	IEC 60250
Relative Permittivity, 1 GHz	13.1	-	IEC 60250
Relative Permittivity, 500 MHz	13.4	-	IEC 60250
Relative Permittivity, 100 MHz	13.6	-	IEC 60250
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.03	%	
Melt Temperature	210 – 215	°C	
Front - Zone 3 Temperature	205 – 215	°C	
Middle - Zone 2 Temperature	200 – 210	°C	
Rear - Zone 1 Temperature	190 – 200	°C	
Mold Temperature	15 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.