

LNPTTM THERMOCOMPTM COMPOUND IB008

IB1008

DESCRIPTION

LNP THERMOCOMP IB008 compound is based on Nylon 6/12 resin containing 40% glass bead.

GENERAL INFORMATION

Features	Low Warpage, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Bead
Polymer Types	Polyamide 612 (Nylon 612)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Personal Accessory
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	74	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.6	%	ISO 527
Flexural Stress, break, 2 mm/min	103	MPa	ISO 178
Flexural Modulus, 2 mm/min	3900	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	8.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	7.9E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	87	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage on Tensile Bar, flow ⁽²⁾	1.4 – 1.8	%	SABIC method
Density	1.36	g/cm ³	ISO 1183
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.12 – 0.2	%	
Melt Temperature	270 – 275	°C	
Front - Zone 3 Temperature	270 – 280	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	260 – 270	°C	
Rear - Zone 1 Temperature	255 – 265	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.