

LNPTM THERMOCOMPTM COMPOUND MB008S

MB-1008 HS

DESCRIPTION

LNP THERMOCOMP MB008S compound is based on Polypropylene (PP) resin containing 40% glass bead. Added features of this grade include: Heat Stabilized.

GENERAL INFORMATION

Features	Heat Stabilized, Low Warpage, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Bead
Polymer Types	Polypropylene, Unspecified (PP, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY

Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Sport/Leisure, Personal Accessory
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	19	MPa	ISO 527
Tensile Stress, break	15	MPa	ISO 527
Tensile Strain, yield	6,1	%	ISO 527
Tensile Strain, break	43.8	%	ISO 527
Tensile Modulus, 1 mm/min	1660	MPa	ISO 527
Flexural Stress	36	MPa	ISO 178
Flexural Modulus	2200	MPa	ISO 178
Tensile Stress, yield	19	MPa	ASTM D638
Tensile Stress, break	15	MPa	ASTM D638
Tensile Strain, yield	6	%	ASTM D638
Tensile Strain, break	160	%	ASTM D638
Tensile Modulus, 50 mm/min	2060	MPa	ASTM D638
Flexural Stress	27	MPa	ASTM D790
Flexural Modulus	2060	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	2	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Multiaxial Impact	1	J	ISO 6603
Izod Impact, notched, 23°C	26	J/m	ASTM D256
Izod Impact, unnotched, 23°C	261	J/m	ASTM D4812
Instrumented Dart Impact Energy @ peak, 23°C	6	J	ASTM D3763

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL ⁽¹⁾			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	61	°C	ISO 75 /Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	103	°C	ISO 75 /Bf
CTE, -40°C to 40°C, flow	6.64E-05	1 / °C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.67E-05	1 / °C	ISO 11359-2
HDT, 0.45 MPa, 3.2 mm, unannealed	102	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	60	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.20E-06	1 / °C	ASTM E831
CTE, -40°C to 40°C, xflow	7.20E-06	1 / °C	ASTM E831
PHYSICAL ⁽¹⁾			
Density	1.21	g / cm ³	ISO 1183
Mold Shrinkage, flow, 24 hrs ⁽²⁾	1.3	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	1.4	%	ISO 294
Density	1.22	g / cm ³	ASTM D792
Mold Shrinkage, flow, 24 hrs ⁽²⁾	1.2 – 1.4	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	1.3 – 1.5	%	ASTM D955
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Melt Temperature	225 – 250	°C	
Front - Zone 3 Temperature	240 – 250	°C	
Middle - Zone 2 Temperature	215 – 225	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	30 – 50	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.