

LNPT[™] THERMOCOMP[™] COMPOUND MX85738

PDX-M-85738

DESCRIPTION

LNP THERMOCOMP MX85738 compound is based on Polypropylene (PP) resin containing 30% glass fiber.

GENERAL INFORMATION

Features	High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polypropylene, Unspecified (PP, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY

Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Sport /Leisure, Personal Accessory
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	66	MPa	ASTM D638
Tensile Strain, break	1.7	%	ASTM D638
Tensile Modulus, 50 mm/min	7760	MPa	ASTM D638
Flexural Stress	96	MPa	ASTM D790
Flexural Modulus	6410	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	267	J/m	ASTM D4812
Izod Impact, notched, 23°C	42	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	148	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.15	g/cm ³	ASTM D792
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.1	%	ASTM D955
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Melt Temperature	225 – 250	°C	
Front - Zone 3 Temperature	240 – 250	°C	
Middle - Zone 2 Temperature	215 – 225	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	30 – 50	°C	



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.