

LNPTTM THERMOCOMPTTM COMPOUND PB006SXS

PB-1006 HS

DESCRIPTION

LNP THERMOCOMP PB006SXS compound is based on Nylon 6 resin containing 30% glass bead. Added features of this grade include: Heat Stabilized.

GENERAL INFORMATION

Features	Heat Stabilized, Low Warpage, High stiffness/Strength
Fillers	Glass Bead
Polymer Types	Polyamide 6 (Nylon 6)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	75	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5 – 7	%	ISO 527
Flexural Stress, yield, 2 mm/min	110	MPa	ISO 178
Flexural Modulus, 2 mm/min	3600	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	152	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	61	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽²⁾	1.4 – 1.6	%	SABIC method
Density	1.33	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	2.5	%	ISO 62-1
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	265 – 275	°C	
Front - Zone 3 Temperature	275 – 290	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	265 – 275	°C	
Rear - Zone 1 Temperature	250 – 260	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.