

LNPT[™] THERMOCOMP[™] COMPOUND QFCOAI

DESCRIPTION

LNPT THERMOCOMP QFCOAI compound is based on Nylon 6/10 resin containing 50% glass fiber. Added feature of this material include: high modulus, high impact, low dielectric constant, low moisture absorption, good dimensional stability and good chemical resistance.

GENERAL INFORMATION

Features	Chemical Resistance, Low Moisture Absorption, Dimensional stability
Fillers	Glass Fiber
Polymer Types	Polyamide 610 (Nylon 610)
Processing Techniques	Injection Molding

INDUSTRY

Industrial

SUB INDUSTRY

Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	161	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3.7	%	ASTM D638
Tensile Modulus, 5 mm/min	11500	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	258	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	10000	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	165	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.8	%	ISO 527
Tensile Modulus, 1 mm/min	11600	MPa	ISO 527
Flexural Strength, 2 mm/min	263	MPa	ISO 178
Flexural Modulus, 2 mm/min	10300	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	155	J/m	ASTM D256
Izod Impact, unnotched, 23°C	1260	J/m	ASTM D4812
Izod Impact, notched 80°10'4 +23°C	15	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'4 0°C	14	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'4 -20°C	14	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80°10'4 +23°C	80	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10'4 0°C	75	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10'4 -20°C	75	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	14.5	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10'4 sp=62mm	84	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	218	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D648

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	205	°C	ISO 75/Af
CTE, -40°C to 90°C, flow	2.0E-5	1/°C	ASTM E83 1
CTE, -40°C to 90°C, xflow	9.5E-5	1/°C	ASTM E83 1
CTE, -40°C to 40°C, flow	1.6E-5	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.0E-5	1/°C	ISO 11359-2
CTE, -40°C to 90°C, flow	1.9E-5	1/°C	ISO 11359-2
CTE, -40°C to 90°C, xflow	9.5E-5	1/°C	ISO 11359-2
PHYSICAL ⁽¹⁾			
Specific Gravity	1.43	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.13	%	ISO 62-1
Moisture Absorption, (23°C/50% RH/24hrs)	0.06	%	ISO 62-4
Moisture Absorption, (23°C/50% RH/Equilibrium)	0.06	%	ISO 62-4
Melt Volume Rate, MVR at 320°C/5.0 kg	56	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow ⁽²⁾	0.25 – 0.3	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.4 – 0.5	%	SABIC method
ELECTRICAL ⁽¹⁾			
Dielectric Constant, 1.9 GHz	3.3	-	SABIC method
Dissipation Factor, 1.9 GHz	0.007	-	SABIC method
INJECTION MOLDING ⁽³⁾			
Drying Temperature	120 – 140	°C	
Drying Time	3 – 4	Hrs	
Melt Temperature	280 – 310	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	290 – 310	°C	
Middle - Zone 2 Temperature	280 – 300	°C	
Rear - Zone 1 Temperature	270 – 290	°C	
Mold Temperature	100 – 130	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.