

LNPTTM THERMOCOMPTM COMPOUND RC003

RC-1003

DESCRIPTION

LNP THERMOCOMP RC003 compound is based on Nylon 6/6 resin containing 15% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION

Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

Electrical and Electronics
Industrial

SUB INDUSTRY

Energy Management, Mobile Phone - Computer - Tablets
Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	170	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	13000	MPa	ISO 527
Flexural Stress, break, 2 mm/min	230	MPa	ISO 178
Flexural Modulus, 2 mm/min	10000	MPa	ISO 178
Hardness, Rockwell L	105	-	ISO 2039-2
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -20°C	4	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	3	kJ/m ²	ISO 180/1A
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	45	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	2.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.1E-04	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/120	255	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	252	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	250	°C	ISO 75/Ae
PHYSICAL ⁽¹⁾			
Mold Shrinkage on Tensile Bar, flow ⁽²⁾	0.1 – 0.2	%	SABIC method
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	5.5	%	ISO 62-1
ELECTRICAL ⁽¹⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Volume Resistivity	1.78E+05	Ω .cm	IEC 60093
Surface Resistivity, ROA	1.78E+05	Ω	IEC 60093
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating ⁽³⁾	1.6	mm	UL 94 by SABIC-IP
Oxygen Index (LOI)	28	%	ISO 4589
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	75 – 85	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.2	%	
Melt Temperature	260 – 290	°C	
Nozzle Temperature	250 – 270	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	270 – 290	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	70 – 120	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL rating shown here is based on internal measurements.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.