

LNPTM THERMOCOMPTM COMPOUND RF006S

RF-1006 HS
REGION ASIA

DESCRIPTION

LNP THERMOCOMP RF006S compound is based on Nylon 6/6 resin containing 30% glass fiber. Added features of this grade include: Heat Stabilized.

GENERAL INFORMATION

Features	Heat Stabilized, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	159	MPa	ASTM D638
Tensile Strain, break	2	%	ASTM D638
Tensile Modulus, 50 mm/min	10270	MPa	ASTM D638
Flexural modulus	10300	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	53	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	247	°C	ASTM D648
Relative Temp Index, Elec ⁽²⁾	130	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	115	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	115	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.4	g/cm ³	ASTM D792
ELECTRICAL ⁽¹⁾			
Hot-Wire Ignition (HWI), PLC 4	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥3	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 1	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
FLAME CHARACTERISTICS ⁽²⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Yellow Card Link	E207780-101281591	-	-
UL Yellow Card Link 2	E207780-103093597	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.