

LNPTTM THERMOCOMPTM COMPOUND WX96784

DESCRIPTION

LNP THERMOCOMP WX96784 compound is based on Polybutylene Terephthalate (PBT) resin containing 25% mineral. Added features of this grade include: Improved CTI, Flame Retardant, Impact Modified.

GENERAL INFORMATION

Features	Flame Retardant, High stiffness/Strength, Impact resistant
Fillers	Mineral
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Automotive Under the Hood
Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	52	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	10 – 15	%	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	3103	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	97	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	117.5	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	77	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Water Absorption, (23°C/24hrs)	.05	%	ASTM D570
Specific Gravity	1.5	-	ASTM D792
Mold Shrinkage, 48 hrs @ 23°C, flow ⁽²⁾	1.10	%	SABIC method
INJECTION MOLDING ⁽³⁾			
Melt Temperature	248 – 276	°C	
Mold Temperature	80 – 93	°C	
Screw Speed	40 – 80	rpm	
Back Pressure	.334	MPa	



- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.