

LNPTTM THERMOCOMPTM COMPOUND ZKC06

DESCRIPTION

LNP THERMOCOMP ZKC06 compound is based on Polyphenylene Ether / Polystyrene (PPE/PS) blend containing 30% minerals and impact modifier. Added features of this grade include: High Dielectric Constant (Dk), Extremely Low Dissipation Factor (Df), Good Ductility and Good Thermal Performance.

GENERAL INFORMATION

Features	Dielectrics, Impact resistant, No PFAS intentionally added
Fillers	Mineral
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Automotive Interiors
Personal Accessory
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	55	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	46	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	8.7	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	14	%	ASTM D638
Tensile Modulus, 50 mm/min	2530	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	85	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	83	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2350	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	56	MPa	ISO 527
Tensile Stress, break, 50 mm/min	49	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7.9	%	ISO 527
Tensile Strain, break, 50 mm/min	16	%	ISO 527
Tensile Modulus, 1 mm/min	2490	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Stress, break, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2620	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	280	J/m	ASTM D256
Izod Impact, notched, -20°C	145	J/m	ASTM D256
Izod Impact, notched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -20°C	13	kJ/m ²	ISO 180/1A

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	173	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	154	°C	ASTM D648
CTE, -40°C to 150°C, flow	6.1E-05	1/°C	ASTM E831
CTE, -40°C to 150°C, xflow	8.7E-05	1/°C	ASTM E831
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	173	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	155	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	65	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.35	g/cm ³	ASTM D792
Mold Shrinkage, flow, 24 hrs ⁽³⁾	0.6 – 0.8	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	0.6 – 0.8	%	ISO 294
Melt Flow Rate, 300°C/5.0 kgf	11	g/10 min	ASTM D1238
Melt Flow Rate, 300°C/10 kgf	36	g/10 min	ASTM D1238
Density	1.35	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.03	%	ISO 62-1
Melt Volume Rate, MVR at 300°C/5.0 kg	9	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 300°C/10.0 kg	30	cm ³ /10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Dielectric Constant, 1.1 GHz	3.7	-	SABIC method
Dielectric Constant, 1.9 GHz	3.7	-	SABIC method
Dielectric Constant, 5 GHz	3.7	-	SABIC method
Dielectric Constant, 10 GHz	3.7	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0009	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0011	-	SABIC method
Dissipation Factor, 5 GHz	0.0019	-	SABIC method
Dissipation Factor, 10 GHz	0.0022	-	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-102719345	-	-
UL Recognized, 94HB Flame Class Rating	1	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	105	°C	
Drying Time	3 – 5	Hrs	
Melt Temperature	295 – 305	°C	
Nozzle Temperature	290 – 295	°C	
Front - Zone 3 Temperature	300 – 305	°C	
Middle - Zone 2 Temperature	290 – 295	°C	
Rear - Zone 1 Temperature	280 – 285	°C	
Mold Temperature	90	°C	
Back Pressure	9	MPa	
Screw Speed	100	rpm	



- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.