

LNPT[™] THERMOCOMP[™] COMPOUND ZKC09

DESCRIPTION

LNP THERMOCOMP ZKC09 compound is based on Polyphenylene Ether / Polystyrene (PPE/PS) blend containing minerals and impact modifier. Added features of this grade include: High Dielectric Constant (Dk), Extremely Low Dissipation Factor (Df), and Good Thermal Performance.

GENERAL INFORMATION

Features	Dielectrics, Low Moisture Absorption, Dimensional stability, No PFAS intentionally added
Fillers	Mineral
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Electrical and Electronics

SUB INDUSTRY

Automotive Interiors
Wireless Communication

TYPICAL PROPERTY VALUES

Revision 20231219

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	55	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	49	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3.3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	6.8	%	ASTM D638
Tensile Modulus, 5 mm/min	3200	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	97	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3060	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	51	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.3	%	ISO 527
Tensile Strain, break, 5 mm/min	7.0	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Strength, 2 mm/min	96	MPa	ISO 178
Flexural Modulus, 2 mm/min	3100	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	146	J/m	ASTM D256
Izod Impact, notched, -30°C	119	J/m	ASTM D256
Izod Impact, unnotched, 23°C	1300	J/m	ASTM D4812
Izod Impact, notched 80°10°4 +23°C	12	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	11	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80°10°4 +23°C	67	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	13	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80°10°4 sp=62mm	9	kJ/m ²	ISO 179/1eA

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	86	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	173	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	159	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	173	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	159	°C	ISO 75/Af
CTE			
-40°C to 40°C, flow	5.4E-5	1/°C	ASTM E831
-40°C to 40°C, xflow	6.9E-5	1/°C	ASTM E831
-40°C to 90°C, flow	5.5E-5	1/°C	ASTM E831
-40°C to 90°C, xflow	7.1E-5	1/°C	ASTM E831
PHYSICAL ⁽¹⁾			
Specific Gravity	1.6	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.07	%	ISO 62-1
Moisture Absorption, (23°C/50% RH/24hrs)	0.02	%	ISO 62-4
Melt Flow Rate, 300°C/5.0 kgf	6.3	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/5.0 kg	4.2	cm ³ /10 min	ASTM D1238
Mold Shrinkage, flow ⁽²⁾	0.7 – 0.9	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.7 – 0.9	%	SABIC method
ELECTRICAL ⁽¹⁾			
Dielectric Constant, 1.1 GHz	4.55	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0011	-	SABIC method
Dielectric Constant, 1.9 GHz	4.55	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0013	-	SABIC method
Dielectric Constant, 5 GHz	4.56	-	SABIC method
Dissipation Factor, 5 GHz	0.0018	-	SABIC method
INJECTION MOLDING ⁽³⁾			
Drying Temperature	105 – 120	°C	
Drying Time	3 – 5	Hrs	
Melt Temperature	290 – 320	°C	
Nozzle Temperature	290 – 320	°C	
Front - Zone 3 Temperature	290 – 320	°C	
Middle - Zone 2 Temperature	280 – 310	°C	
Rear - Zone 1 Temperature	270 – 300	°C	
Mold Temperature	90 – 120	°C	
Back Pressure	0.3 – 0.9	MPa	
Screw Speed	50 – 150	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.