

LNPTTM THERMOTUFTM COMPOUND AX06401

AF-1004 HI HS

DESCRIPTION

THERMOTUF AX06401 compound is based on Acrylonitrile Butadiene Styrene (ABS) resin containing 20% glass fiber. Added features of this grade include: Improved Toughness.

GENERAL INFORMATION

Applications	Commercial Appliance
Features	High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Acrylonitrile Butadiene Styrene (ABS)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Industrial

SUB INDUSTRY

Building Component
Home Appliances
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Modulus, 1 mm/min	7000	MPa	ISO 527
Tensile Stress, break, 5 mm/min	85	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.9	%	ISO 527
Flexural Modulus, 2 mm/min	6600	MPa	ISO 178
Flexural Strength, 2 mm/min	146	MPa	ISO 178
Tensile Stress, brk, Type I, 5 mm/min	93	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D638
Tensile Modulus, 5 mm/min	6800	MPa	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	5650	MPa	ASTM D790
Flexural Strength, 1.3 mm/min, 50 mm span	141	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	39	kJ/m ²	ISO 180/1U
Izod Impact, notched, 23°C	90	J/m	ASTM D256
Izod Impact, unnotched, 23°C	450	J/m	ASTM D4812
Instrumented Dart Impact Total Energy, 23°C	11	J	ASTM D3763
Instrumented Dart Impact Energy @ peak, 23°C	10	J	ASTM D3763
Instrumented Dart Impact Peak Force, 23°C	626	N	ASTM D3763
THERMAL ⁽¹⁾			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	102	°C	ISO 75/Af

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate A/50	117	°C	ASTM D1525
CTE, -40°C to 40°C, flow	3.93E-05	1 / °C	ASTM E831
CTE, -40°C to 40°C, xflow	8.07E-05	1 / °C	ASTM E831
Vicat Softening Temp, Rate A/50	117	°C	ISO 306
HDT, 1.82 MPa, 3.2mm, unannealed	102	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.25	g / cm ³	ISO 1183
Moisture Absorption, (23°C/50% RH/24hrs)	0.04	%	ISO 62-4
Mold Shrinkage, flow ⁽²⁾	1.64	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	1.73	%	SABIC method
INJECTION MOLDING ⁽³⁾			
Drying Temperature	70 – 90	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	205 – 215	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Front - Zone 3 Temperature	265 – 275	°C	
Mold Temperature	70 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	
Vent Depth	–	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.