

LNPTTM THERMOTUFTM COMPOUND V1000

V-1000

DESCRIPTION

LNP THERMOTUF V1000 compound is based on unfilled Super Tough Nylon resin. Added features of this grade include: Impact Modified.

GENERAL INFORMATION

Features	Impact resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Consumer
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	45	MPa	ASTM D638
Tensile Stress, break	50	MPa	ASTM D638
Tensile Strain, yield	4.6	%	ASTM D638
Tensile Strain, break	60.3	%	ASTM D638
Tensile Modulus, 50 mm/min	1930	MPa	ASTM D638
Flexural Stress	74	MPa	ASTM D790
Flexural Modulus	1930	MPa	ASTM D790
Tensile Stress, yield	44	MPa	ISO 527
Tensile Stress, break	50	MPa	ISO 527
Tensile Strain, yield	17.1	%	ISO 527
Tensile Strain, break	168.1	%	ISO 527
Tensile Modulus, 1 mm/min	1800	MPa	ISO 527
Flexural Stress	64	MPa	ISO 178
Flexural Modulus	1700	MPa	ISO 178
IMPACT ⁽¹⁾			
Instrumented Dart Impact Energy @ peak, 23°C	56	J	ASTM D3763
Multiaxial Impact	77	J	ISO 6603
Izod Impact, unnotched 80°10°4 +23°C	137	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	84	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	53	°C	ASTM D648

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	1.27E-04	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	1.26E-04	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	1.27E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.26E-04	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	56	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	110	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	75	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	85	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.073	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.8	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽³⁾	1.3 – 1.5	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	1.3 – 1.5	%	ASTM D955
Mold Shrinkage, flow, 24 hrs ⁽³⁾	1.3 – 1.5	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	1.3 – 1.5	%	ISO 294
Density	1.07	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.37	%	ISO 62
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-101282752	-	-
UL Yellow Card Link 2	E207780-101282736	-	-
UL Recognized, 94HB Flame Class Rating	≥0.75	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	270 – 295	°C	
Front - Zone 3 Temperature	290 – 300	°C	
Middle - Zone 2 Temperature	270 – 280	°C	
Rear - Zone 1 Temperature	260 – 270	°C	
Mold Temperature	50 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	10 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.