

LNPT[™] VERTON[™] COMPOUND MVO0CS

MFX70012HS

DESCRIPTION

LNP VERTON MVO0CS is a compound based on Polypropylene (PP) resin containing 60% long glass fiber. Added features include Chemically Coupled, Heat Stabilized and Structural.

GENERAL INFORMATION

Features	Heat Stabilized, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polypropylene, Unspecified (PP, Unspecified)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Building and Construction
Consumer
Industrial

SUB INDUSTRY

Automotive Exteriors
Water Management
Sport/Leisure, Home Appliances, Commercial Appliance
Industrial General

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	120	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.2	%	ISO 527
Tensile Modulus, 1 mm/min	15100	MPa	ISO 527
Flexural Modulus, 2 mm/min	13700	MPa	ISO 178
Flexural Stress, break, 2 mm/min	175	MPa	ISO 178
Tensile Modulus, 5 mm/min	17300	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	1.1	%	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	120	MPa	ASTM D638
Flexural Modulus, 1.3 mm/min, 50 mm span	13800	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	170	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	135	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	39	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	13	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	29	kJ/m ²	ISO 179/1eU
Izod Impact, notched, 23°C	155	J/m	ASTM D256
Izod Impact, unnotched, 23°C	620	J/m	ASTM D4812
THERMAL ⁽¹⁾			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	154	°C	ISO 75/Af

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Bf
HDT, 1.82 MPa, 3.2mm, unannealed	156	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.47	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.6	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	0.8	%	ASTM D955
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Melt Temperature	220 – 250	°C	
Front - Zone 3 Temperature	250 – 260	°C	
Middle - Zone 2 Temperature	245 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Mold Temperature	40 – 65	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.