

LNPT[™] VERTON[™] COMPOUND RV007E

RF-7007 EM

DESCRIPTION

LNP VERTON RV007E is a compound based on Polyamide 66 (Nylon 66) resin containing 35% long glass fiber. Added features include Easy Molding and Structural.

GENERAL INFORMATION

Features	Good Processability, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Building and Construction
Consumer
Industrial

SUB INDUSTRY

Automotive Exteriors
Building Component
Sport/Leisure, Home Appliances, Commercial Appliance
Electrical, Industrial General

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	214	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.1	%	ISO 527
Flexural Stress, break, 2 mm/min	309	MPa	ISO 178
Flexural Modulus, 2 mm/min	10200	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	29	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	252	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	95	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	75	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.42	g/cm ³	ISO 1183
ELECTRICAL ⁽²⁾			
Hot-Wire Ignition (HWI), PLC 0	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	0	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	<u>E45329-101282651</u>	-	-
UL Recognized, 94HB Flame Class Rating ⁽²⁾	≥0.75	mm	UL 94
Glow Wire Flammability Index 960°C, passes at ⁽²⁾	0.75	mm	IEC 60695-2-12
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	290 – 305	°C	
Front - Zone 3 Temperature	290 – 300	°C	
Middle - Zone 2 Temperature	290 – 300	°C	
Rear - Zone 1 Temperature	280 – 295	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.