

LNPTM VERTONTM COMPOUND RVL28

RFL-8028 EM HS

DESCRIPTION

LNP VERTON RVL28 is a compound based on Polyamide 66 (Nylon 66) resin containing 40% long glass fiber, 10% PTFE. Added features include Easy Molding, Heat Stabilized, Wear Resistant and Structural.

GENERAL INFORMATION

Features	Good Processability, Heat Stabilized, Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Building and Construction
Consumer
Industrial

SUB INDUSTRY

Automotive Exteriors
Building Component
Sport/Leisure, Home Appliances
Electrical, Industrial General

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	228	MPa	ISO 527
Tensile Stress, break	228	MPa	ISO 527
Tensile Strain, yield	2.4	%	ISO 527
Tensile Strain, break	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	13230	MPa	ISO 527
Flexural Stress	351	MPa	ISO 178
Flexural Modulus	13000	MPa	ISO 178
Tensile Stress, yield	220	MPa	ASTM D638
Tensile Stress, break	220	MPa	ASTM D638
Tensile Strain, yield	2.3	%	ASTM D638
Tensile Strain, break	2.3	%	ASTM D638
Tensile Modulus, 50 mm/min	14470	MPa	ASTM D638
Flexural Stress	337	MPa	ASTM D790
Flexural modulus	12200	MPa	ASTM D790
IMPACT			
Izod Impact, notched 80*10*4 +23°C	23	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	93	kJ/m ²	ISO 180/1U
Multiaxial Impact	7	J	ISO 6603
Izod Impact, notched, 23°C	265	J/m	ASTM D256
Izod Impact, unnotched, 23°C	1409	J/m	ASTM D4812

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Instrumented Dart Impact Energy @ peak, 23°C	14	J	ASTM D3763
THERMAL			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	255	°C	ISO 75 /Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	259	°C	ISO 75 /Bf
CTE, -40°C to 40°C, flow	2.10E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.90E-05	1/°C	ISO 11359-2
HDT, 0.45 MPa, 3.2 mm, unannealed	256	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	252	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.16E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	4.86E-05	1/°C	ASTM E831
PHYSICAL			
Density	1.57	g/cm ³	ISO 1183
Mold Shrinkage, flow, 24 hrs	0.33	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.77	%	ISO 294
Density	1.57	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.5	%	ASTM D570
Mold Shrinkage, flow, 24 hrs	0.2 – 0.4	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs	0.7 – 0.9	%	ASTM D955
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	290 – 305	°C	
Front - Zone 3 Temperature	290 – 300	°C	
Middle - Zone 2 Temperature	290 – 300	°C	
Rear - Zone 1 Temperature	280 – 295	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.