

LNPT[™] VERTON[™] COMPOUND RVL36

RFL-8036

DESCRIPTION

LNP VERTON RVL36 is a compound based on Polyamide 66 (Nylon 66) resin containing 30% long glass fiber and 15% PTFE. Added features include Wear Resistant and Structural.

GENERAL INFORMATION

Features	Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, PTFE
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Building and Construction
Consumer
Industrial

SUB INDUSTRY

Automotive Exteriors
Building Component
Sport/Leisure, Home Appliances, Commercial Appliance
Electrical, Industrial General

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	185	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.9	%	ISO 527
Flexural Stress, yield, 2 mm/min	265	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3.3	%	ISO 178
Flexural Modulus, 2 mm/min	8900	MPa	ISO 178
Flexural Strain, break, 2 mm/min, 60°C	3.9	%	ISO 178
Flexural Strain, break, 2 mm/min, 100°C	4	%	ISO 178
Flexural Strain, break, 2 mm/min, 150°C	3.6	%	ISO 178
Flexural Strain, break, 2 mm/min, 200°C	3.4	%	ISO 178
Flexural Stress, yield, 2 mm/min, 60°C	208	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 100°C	155	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 150°C	129	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 200°C	105	MPa	ISO 178
Flexural Modulus, 2 mm/min, 60°C	7100	MPa	ISO 178
Flexural Modulus, 2 mm/min, 100°C	5800	MPa	ISO 178
Flexural Modulus, 2 mm/min, 150°C	5200	MPa	ISO 178
Flexural Modulus, 2 mm/min, 200°C	4800	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*3 -40°C	15	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	54	kJ/m ²	ISO 180/1U

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*4 -40°C	50	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	16	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
Specific Heat	1846	J/kg-K	ASTM E1269
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	258	°C	ISO 75/Af
Thermal Conductivity	0.25	W/m-K	ASTM D5930
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.25	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	0.69	%	ISO 294
Wear Factor Washer	12	10 ⁻⁴ in ³ -min/ft-lb-hr	ASTM D3702 Modified: Manual
Density	1.53	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	1.37	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.4	%	ISO 62
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	290 – 305	°C	
Front - Zone 3 Temperature	290 – 300	°C	
Middle - Zone 2 Temperature	290 – 300	°C	
Rear - Zone 1 Temperature	280 – 295	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.