

LNPT[™] VERTON[™] COMPOUND RVN1AESP

DESCRIPTION

LNP VERTON RVN1AESP is a compound based on Polyamide 66 (Nylon 66) resin containing 50% long glass fiber and proprietary lubricant. Added features include Easy Molding, Wear Resistant and Structural.

GENERAL INFORMATION

Features	Wear resistant, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber, Proprietary Filler
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

INDUSTRY

Automotive
Building and Construction
Consumer
Industrial

SUB INDUSTRY

Automotive Exteriors
Building Component
Sport/Leisure, Home Appliances, Commercial Appliance
Electrical, Industrial General

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	250	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.1	%	ASTM D638
Tensile Modulus, 5 mm/min	16700	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	320	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	11800	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	235	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Tensile Modulus, 1 mm/min	17000	MPa	ISO 527
Flexural Strength, 2 mm/min	330	MPa	ISO 178
Flexural Modulus, 2 mm/min	11300	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	1160	J/m	ASTM D4812
Izod Impact, notched, 23°C	270	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	12	J	ASTM D3763
Izod Impact, notched 80°10°4 +23°C	35	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -40°C	40	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80°10°4 +23°C	90	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	35	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10°4 sp=62mm	95	kJ/m ²	ISO 179/1eU
Multiaxial Impact ⁽²⁾	13	J	ISO 6603
THERMAL ⁽¹⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS[™]

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	240	°C	ISO 306
Vicat Softening Temp, Rate B/120	235	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	250	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	245	°C	ISO 75/Af
CTE, -40°C to 40°C, flow	1.4E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.7E-05	1/°C	ISO 11359-2
PHYSICAL ⁽¹⁾			
Moisture Absorption, (23°C/50% RH/24 hrs)	0.1	%	ASTM D570
Water Absorption, (23°C/24hrs)	0.8 – 0.9	%	ASTM D570
Specific Gravity	1.6	-	ASTM D792
Density	1.6	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.3	%	ISO 62
Water Absorption, (23°C/saturated)	4.4	%	ISO 62-1
Mold Shrinkage, flow, 24 hrs ⁽³⁾	0.2 – 0.3	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	0.7 – 0.8	%	ISO 294
Wear Factor Washer	33	10 ⁻¹⁰ in ⁴ -min/ft-lb-hr	ASTM D3702 Modified: Instr.
Dynamic COF	0.58	-	ASTM D3702 Modified: Instr.
Static COF	0.71	-	ASTM D3702 Modified: Instr.
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	290 – 305	°C	
Nozzle Temperature	290 – 305	°C	
Front - Zone 3 Temperature	290 – 300	°C	
Middle - Zone 2 Temperature	290 – 300	°C	
Rear - Zone 1 Temperature	280 – 295	°C	
Hopper Temperature	40	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Test speed = 6.7m/s

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.