

NORYL GTX™ RESIN GTX678

REGION AMERICAS

DESCRIPTION

NORYL GTX678 resin is a conductive, high performance non-reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade is optimized for primer-less electrostatic and powder coat painting, and it is UL 5VA rated with a non-brominated, non-chlorinated FR package. NORYL GTX678 resin exhibits an excellent balance of conductivity, high heat resistance, good ductility, and is heat stabilized. This material is an excellent candidate for non-automotive painted applications such as office furniture, PVC/metal replacement, lighting ballast housings / enclosures, and appliance exteriors.

GENERAL INFORMATION

Features

Flame Retardant, Chemical Resistance, Electrically Conductive, Hydrolytic Stability, Low Warpage, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Aesthetics/Visual effects, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength, High temperature resistance, Impact resistant

Fillers

Conductive agent

Polymer Types

Polyphenylene Ether + PA (PPE+Nylon)

Processing Techniques

Injection Molding

INDUSTRY

Building and Construction

Consumer

Electrical and Electronics

Industrial

SUB INDUSTRY

Building Component

Home Appliances, Commercial Appliance

Mobile Phone - Computer - Tablets, Lighting

Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	52	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	12	%	ASTM D638
Tensile Modulus, 5 mm/min	2900	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	95	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2600	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	58	MPa	ISO 527
Tensile Stress, break, 50 mm/min	52	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	12	%	ISO 527
Tensile Modulus, 1 mm/min	2900	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	2600	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	100	J/m	ASTM D256

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched, -30°C	70	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	60	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	12	kJ/m ²	ISO 179/1eA
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	198	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	195	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.8E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E831
Specific Heat	1.4	J/g·°C	ASTM C351
Thermal Conductivity	0.2	W/m·°C	ASTM C177
CTE, 23°C to 60°C, flow	8.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASS	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	197	°C	ISO 306
Vicat Softening Temp, Rate B/120	195	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	191	°C	ISO 75/Bf
Relative Temp Index, Elec ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	65	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.12	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	1.3 – 1.5	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	7.8	g/10 min	ASTM D1238
Density	1.12	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	4	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.5	%	ISO 62
Melt Volume Rate, MVR at 300°C/5.0 kg	7	cm ³ /10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Volume Resistivity	4.E+03	Ω.cm	ASTM D257
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E121562-516521	-	-
UL Recognized, 94-5VA Flame Class Rating	≥2	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥2	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥1.5	mm	UL 94
Glow Wire Flammability Index, 1.0 mm	825	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	825	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	800	°C	IEC 60695-2-13
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	95 – 105	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.07	%	
Minimum Moisture Content	0.02	%	
Melt Temperature	275 – 300	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	270 – 300	°C	
Middle - Zone 2 Temperature	265 – 300	°C	
Rear - Zone 1 Temperature	260 – 300	°C	
Mold Temperature	65 – 95	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	
PROFILE EXTRUSION			
Drying Temperature	105 – 110	°C	
Drying Time	8	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.03	%	
Melt Temperature	245 – 260	°C	
Barrel - Zone 1 Temperature	245 – 260	°C	
Barrel - Zone 2 Temperature	245 – 260	°C	
Barrel - Zone 3 Temperature	245 – 260	°C	
Barrel - Zone 4 Temperature	245 – 260	°C	
Adapter Temperature	245 – 260	°C	
Die Temperature	245 – 260	°C	
Calibrator Temperature	35 – 75	°C	
Water Bath Temperature	40 - 50	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.