

NORYL GTX™ RESIN GTX830

REGION AMERICAS

DESCRIPTION

NORYL GTX830 resin is a 30% glass fiber reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade has high stiffness (flexural modulus 8200 MPa), excellent chemical resistance, and high heat resistance. NORYL GTX830 resin is an excellent candidate for a wide variety of applications including automotive under the bonnet applications and water meter housings.

GENERAL INFORMATION

Features

Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Moisture Absorption, Low Specific Gravity, Potable water safe, Dimensional stability, High stiffness/Strength, High temperature resistance, No PFAS intentionally added

Fillers

Glass Fiber

Polymer Types

Polyphenylene Ether + PA (PPE+Nylon)

Processing Techniques

Injection Molding

INDUSTRY

Automotive

Building and Construction

Electrical and Electronics

Industrial

SUB INDUSTRY

Automotive Under the Hood

Water Management

Electronic Components

Electrical

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Nominal Stress, yld, Type I, 5 mm/min	151	MPa	ASTM D638
Nominal Stress, brk, Type I, 5 mm/min	158	MPa	ASTM D638
Nominal Strain, brk, 5 mm/min	7	%	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	248	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	8580	MPa	ASTM D790
Hardness, Rockwell R	120	-	ASTM D785
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	106	J/m	ASTM D256
Izod Impact, notched, -30°C	80	J/m	ASTM D256
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	248	°C	ASTM D1525
HDT, 0.45 MPa, 6.4 mm, unannealed	254	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	240	°C	ASTM D648
CTE, -20°C to 150°C, flow	0.0000198 – 0.0000306	1/°C	ASTM E831
PHYSICAL ⁽¹⁾			
Specific Gravity	1.33	-	ASTM D792
Density	1.328	g/cm ³	ASTM D792
Moisture Absorption, (50% RH, Equilibrium)	1	%	ASTM D570

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption, (23°C/50% RH/24 hrs)	0.5	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.2 – 0.3	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽²⁾	0.65 – 0.85	%	SABIC method
ELECTRICAL ⁽¹⁾			
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 2	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥1.5	mm	UL 746A
FLAME CHARACTERISTICS ⁽³⁾			
UL Yellow Card Link	E121562-220762	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.07	%	
Minimum Moisture Content	0.02	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	275 – 305	°C	
Middle - Zone 2 Temperature	270 – 305	°C	
Rear - Zone 1 Temperature	265 – 305	°C	
Mold Temperature	75 – 120	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.