

NORYL GTX™ RESIN GTX8408

REGION AMERICAS

DESCRIPTION

NORYL GTX8408 resin is an 8% glass reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade exhibits high elongation, excellent chemical resistance, high heat resistance, and flow. NORYL GTX8408 resin is an excellent candidate for a wide variety of structural and electrical connector applications.

GENERAL INFORMATION

Features	Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PA (PPE+Nylon)
Processing Techniques	Injection Molding

INDUSTRY

Building and Construction
Electrical and Electronics
Industrial

SUB INDUSTRY

Building Component
Electronic Components, Mobile Phone - Computer - Tablets
Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	84	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	80	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	4.3	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	10.2	%	ASTM D638
Tensile Modulus, 5 mm/min	3560	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	92	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3320	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	87	MPa	ISO 527
Tensile Stress, break, 5 mm/min	82	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.5	%	ISO 527
Tensile Strain, break, 5 mm/min	10	%	ISO 527
Tensile Modulus, 1 mm/min	4000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	133	MPa	ISO 178
Flexural Modulus, 2 mm/min	3520	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	82	J/m	ASTM D256
Izod Impact, notched, -30°C	45	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	4	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	7	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	3	kJ/m²	ISO 180/1A

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m ²	ISO 179/1eA
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	224	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	239	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.83E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.46E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	6.83E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.46E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	224	°C	ISO 306
Vicat Softening Temp, Rate B/120	224	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	240	°C	ISO 75/Bf
PHYSICAL ⁽¹⁾			
Specific Gravity	1.15	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	26.3	g/10 min	ASTM D1238
Density	1.15	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.35	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	22	cm ³ /10 min	ISO 1133
INJECTION MOLDING ⁽³⁾			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.07	%	
Minimum Moisture Content	0.02	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	275 – 305	°C	
Middle - Zone 2 Temperature	270 – 305	°C	
Rear - Zone 1 Temperature	265 – 305	°C	
Mold Temperature	75 – 120	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.