

NORYL™ RESIN CN5246

REGION ASIA

DESCRIPTION

NORYL CN5246 resin is a 30% mineral and glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This high modulus, injection moldable grade contains non-brominated, non-chlorinated flame retardant and carries a UL94 flame rating of 5VB at 2mm and V1 at 1.5mm. NORYL CN5246 resin exhibits good dimensional stability, low moisture absorption, high rigidity and is an excellent candidate for printer chassis applications.

GENERAL INFORMATION

Features

Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength

Fillers

Glass Fiber, Mineral

Polymer Types

Polyphenylene Ether + PS (PPE+PS)

Processing Techniques

Injection Molding

INDUSTRY

Electrical and Electronics

Industrial

SUB INDUSTRY

Mobile Phone - Computer - Tablets

Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	108	MPa	SABIC - Japan Method
Tensile Strain, break	7	%	SABIC - Japan Method
Flexural Stress	152	MPa	ASTM D790
Flexural Modulus	8230	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	68	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 6.4 mm, unannealed	125	°C	ASTM D648
CTE, -30°C to 30°C	2.40E-05 – 3.40E-05	1/°C	TMA
Relative Temp Index, Elec ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	65	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.33	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.25 – 0.3	%	SABIC method
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-228542	-	-
UL Recognized, 94-5VB Flame Class Rating	≥2	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥1.5	mm	UL 94

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	100	°C	
Drying Time	3 – 4	Hrs	
Melt Temperature	280 – 310	°C	
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	280 – 310	°C	
Middle - Zone 2 Temperature	270 – 300	°C	
Rear - Zone 1 Temperature	260 – 290	°C	
Mold Temperature	80 – 100	°C	
Back Pressure	0.5 – 1.2	MPa	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.