

NORYL™ RESIN GFN2F

REGION AMERICAS

DESCRIPTION

NORYL GFN2F resin is a 20% glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability. NORYL GFN2F carries a UL746C outdoor suitability rating of F1 along with FDA food contact compliance and NSF 61 listings in several colors. The properties of this material makes it an excellent candidate for water management applications such as water filter and meter components, pump housings / impellers, shower + faucet, and valves.*See NORYL GFN2 resin for NON FDA / NSF version.

GENERAL INFORMATION

Features

Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Corrosivity, Low Moisture Absorption, Low Specific Gravity, Food contact, Potable water safe, Dimensional stability, High stiffness/Strength, No PFAS intentionally added

Fillers

Glass Fiber

Polymer Types

Polyphenylene Ether + PS (PPE+PS)

Processing Techniques

Injection Molding

INDUSTRY

Building and Construction

Hygiene and Healthcare

SUB INDUSTRY

Water Management

Personal and Professional Hygiene

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 5 mm/min	90	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.6	%	ASTM D638
Tensile Modulus, 5 mm/min	6200	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	160	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	5800	MPa	ASTM D790
Hardness, Rockwell L	106	-	ASTM D785
Tensile Stress, break, 5 mm/min	97	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	7070	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	167	MPa	ISO 178
Flexural Modulus, 2 mm/min	6540	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	650	J/m	ASTM D4812
Izod Impact, notched, 23°C	119	J/m	ASTM D256
Izod Impact, notched, -40°C	96	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	22	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	11	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	11	kJ/m ²	ISO 179/2C
THERMAL ⁽¹⁾			

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 3.2 mm, unannealed	140	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	143	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	137	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.89E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.26E-05	1/°C	ASTM E831
Vicat Softening Temp, Rate B/50	143	°C	ISO 306
Vicat Softening Temp, Rate B/120	146	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	143	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	137	°C	ISO 75/Ae
Relative Temp Index, Elec ⁽²⁾	90	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	90	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	90	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.2	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.2 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	9	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/5.0 kg	8	cm³/10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Dielectric Strength, in oil, 3.2 mm	16.5	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	2.86	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0008	-	ASTM D150
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥6	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥6	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 4	≥1.5	mm	UL 746A
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D495
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	<u>E121562-221161</u>	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C
Oxygen Index (LOI)	26	%	ASTM D2863
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 325	°C	
Nozzle Temperature	300 – 325	°C	
Front - Zone 3 Temperature	290 – 325	°C	
Middle - Zone 2 Temperature	275 – 320	°C	
Rear - Zone 1 Temperature	265 – 315	°C	
Mold Temperature	80 – 110	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.