

NORYL™ RESIN HFM3015P

REGION ASIA

DESCRIPTION

NORYL HFM3015P resin is a 30% glass fiber and mineral reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection moldable grade contains non-brominated, non-chlorinated flame retardant and carries a UL94 flame rating of V1 at 1.5mm. NORYL HFM3015P resin exhibits exceptional dimensional stability, high stiffness and strength, strong electrical performance, very low moisture absorption, and hydrolytic stability. This material is an excellent candidate for internal structural parts such as chassis.

GENERAL INFORMATION

Features

Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Aesthetics/Visual effects, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added

Fillers

Glass Fiber, Mineral

Polymer Types

Polyphenylene Ether + PS (PPE+PS)

Processing Techniques

Injection Molding

INDUSTRY

Electrical and Electronics

SUB INDUSTRY

Electronic Components, Mobile Phone - Computer - Tablets

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield	98	MPa	SABIC - Japan Method
Tensile Strain, break	4 – 6	%	SABIC - Japan Method
Flexural Stress	137	MPa	ASTM D790
Flexural Modulus	7640	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	58	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 6.4 mm, unannealed	110	°C	ASTM D648
CTE, -30°C to 30°C	0.000025 – 0.000035	1 / °C	TMA
PHYSICAL ⁽¹⁾			
Specific Gravity	1.32	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.25 – 0.3	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	48.3	g/10 min	ASTM D1238
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	Hrs	
Melt Temperature	260 – 300	°C	
Nozzle Temperature	260 – 300	°C	
Front - Zone 3 Temperature	260 – 300	°C	

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	240 – 280	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.5 – 1.2	MPa	
Screw Speed	40 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.