

NORYL™ RESIN PX0844

REGION AMERICAS

DESCRIPTION

NORYL PX0844 resin is a non-reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This grade exhibits very low moisture absorption, hydrolytic stability, dimensional stability, good foam adhesion, and property retention over a wide temperature range. NORYL PX0844 resin is inherently UL94 HB and is an excellent candidate for automotive interior applications such as instrument panels, audio components, speaker housings, and interior trim. *see NORYL PX0888 resin for higher heat resistance.

GENERAL INFORMATION

Features	Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY

Automotive

SUB INDUSTRY

Automotive Interiors

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	49	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	44	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	30	%	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D638
Tensile Modulus, 5 mm/min	2290	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	80	MPa	ASTM D790
Flexural Stress, yld, 2.6 mm/min, 100 mm span	75	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2550	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	2240	MPa	ASTM D790
Hardness, Rockwell R	114	-	ASTM D785
Tensile Stress, yield	47	MPa	ISO 527
Tensile Stress, break	43	MPa	ISO 527
Tensile Strain, yield	2.9	%	ISO 527
Tensile Strain, break	43	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress	78	MPa	ISO 178
Flexural Modulus	2400	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	234	J/m	ASTM D256
Izod Impact, notched, -30°C	175	J/m	ASTM D256
Izod Impact, notched, -40°C	133	J/m	ASTM D256

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Instrumented Dart Impact Total Energy, 23°C	40	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	17	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	17	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	10	kJ/m ²	ISO 179/2C
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	120	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	105	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	121	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	112	°C	ASTM D648
CTE, 0°C to 100°C, flow	7.38E-05	1/°C	ASTM E831
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
Vicat Softening Temp, Rate B/120	128	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	122	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	107	°C	ISO 75/Ae
PHYSICAL ⁽¹⁾			
Specific Gravity	1.06	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.1	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	13.7	g/10 min	ASTM D1238
INJECTION MOLDING ⁽³⁾			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	275 – 305	°C	
Nozzle Temperature	275 – 305	°C	
Front - Zone 3 Temperature	265 – 305	°C	
Middle - Zone 2 Temperature	255 – 300	°C	
Rear - Zone 1 Temperature	245 – 295	°C	
Mold Temperature	70 – 100	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	
Vent Depth	0.038 – 0.051	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.