

ULTEM™ RESIN 1040P

REGION AMERICAS

DESCRIPTION

Enhanced Flow Polyetherimide in 350 micron powder.

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	97	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	97	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	10	%	ASTM D638
Tensile Modulus, 5 mm/min	3440	MPa	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	159	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3400	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	90	MPa	ISO 527
Tensile Stress, break, 5 mm/min	90	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	10	%	ISO 527
Tensile Modulus, 1 mm/min	3000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	150	MPa	ISO 178
Flexural Modulus, 2 mm/min	3000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	470	J/m	ASTM D4812
Izod Impact, notched, 23°C	21	J/m	ASTM D256
Izod Impact, notched, -30°C	20	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	30	J	ASTM D3763
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	205	°C	ASTM D1525
HDT, 1.82 MPa, 6.4 mm, unannealed	196	°C	ASTM D648
CTE, -40°C to 40°C, flow	5.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	5.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	5.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	211	°C	ISO 306
Vicat Softening Temp, Rate B/120	212	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	190	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.27	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 295°C/6.6 kgf	6.6	g/10 min	ASTM D1238
Density	1.27	g/cm ³	ISO 1183

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, (23°C/saturated)	1.25	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.7	%	ISO 62
Melt Volume Rate, MVR at 220°C/5.0 kg	10	cm ³ /10 min	ISO 1133

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.