

ULTEM™ RESIN AR9300

REGION EUROPE

DESCRIPTION

30% Glass fiber filled, standard flow Polyetherimide (Tg 217°C). Meets FAR 25.853 and OSU 65/65 with low toxicity, smoke, and flame evolution. ECO Conforming.

INDUSTRY	SUB INDUSTRY
Automotive	Aerospace
Mass Transportation	Rail

TYPICAL PROPERTY VALUES

Revision 2023 1109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break, 5 mm/min	165	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	9500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	225	MPa	ISO 178
Flexural Modulus, 2 mm/min	8500	MPa	ISO 178
Ball Indentation Hardness, H358/30	160	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched 80°10°4 +23°C	35	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80°10°4 -30°C	35	kJ/m²	ISO 180/1U
Charpy 23°C, Unnotch Edgew 80°10°4 sp=62mm	40	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10°4 sp=62mm	40	kJ/m²	ISO 179/1eU
THERMAL			
Thermal Conductivity	0.29	W/m·°C	ISO 8302
CTE, 23°C to 150°C, flow	1.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	4.2E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	210	°C	ISO 306
Vicat Softening Temp, Rate B/120	215	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120°10°4 sp=100mm	212	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120°10°4 sp=100mm	208	°C	ISO 75/Ae
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.4	%	SABIC method
Density	1.49	g/cm³	ISO 1183
Melt Volume Rate, MVR at 360°C/5.0 kg	6	cm³/10 min	ISO 1133
FLAME CHARACTERISTICS			
OSU total heat release (2 minute test)	5	kW-min/m²	FAR 25.853
OSU peak heat release rate (5 minute test)	40	kW/m²	FAR 25.853
INJECTION MOLDING			



PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	350 – 410	°C	
Front - Zone 3 Temperature	350 – 410	°C	
Middle - Zone 2 Temperature	350 – 400	°C	
Rear - Zone 1 Temperature	350 – 370	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	135 – 140	°C	

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.