

ULTEM™ RESIN SF2270

DESCRIPTION

20% Glass fiber filled, super high flow (highest flow) polyetherimide(PEI) (TG 217degC) with internal mold release, ECO conforming, UL94 V0 listing.

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Flexural Stress, yld, 1.3 mm/min, 50 mm span	189	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	189	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	8000	MPa	ASTM D790
Tensile Stress, brk, Type I, 5 mm/min	145	MPa	ASTM D638
Tensile Modulus, 5 mm/min	9247	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D638
Flexural Stress, yield, 2 mm/min	174	MPa	ISO 178
Flexural Stress, break, 2 mm/min	173	MPa	ISO 178
Flexural Modulus, 2 mm/min	7102	MPa	ISO 178
Tensile Stress, break, 5 mm/min	131	MPa	ISO 527
Tensile Modulus, 1 mm/min	9102	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
IMPACT			
Izod Impact, notched, 23°C	67	J/m	ASTM D256
Izod Impact, unnotched, 23°C	323	J/m	ASTM D4812
Izod Impact, notched 80°10°4 +23°C	7.7	kJ/m²	ISO 180/1A
Izod Impact, unnotched 80°10°4 +23°C	28.8	kJ/m²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80°10°4 sp=62mm	6.9	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10°4 sp=62mm	32.9	kJ/m²	ISO 179/1eU
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	202	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	199	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	207	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	204	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	202	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80°10°4 sp=64mm	208	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/50	211	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	213	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	210	°C	ISO 306
Vicat Softening Temp, Rate B/120	212	°C	ISO 306
CTE, -40°C to 150°C, flow	2.4E-05	1/°C	ASTM E831
CTE, -40°C to 150°C, xflow	6.0E-05	1/°C	ASTM E831
CTE, 23°C to 150°C, flow	1.77E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	6.77E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec	105	°C	UL 746B
Relative Temp Index, Mech w/impact	105	°C	UL 746B

© 2023 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Mech w/o impact	105	°C	UL 746B
PHYSICAL			
Density	1.435	g/cm ³	ISO 1183
Mold Shrinkage, flow	0.33	%	SABIC method
Mold Shrinkage, xflow	0.45	%	SABIC method
Moisture Absorption, (23°C/50% RH/24hrs)	0.04	%	ISO 62-4
Water Absorption, (23°C/24hrs)	0.12	%	ASTM D570
Specific Gravity	1.441	-	ASTM D792
Melt Volume Rate, MVR at 360°C/2.16 kg	17	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 337°C/6.7 kg	30	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 345°C/10.0 kg	87	cm ³ /10 min	ISO 1133
Melt Flow Rate, 337°C/6.7 kgf	43	g/10 min	ASTM D1238
Melt Flow Rate, 345°C/10 kgf	110	g/10 min	ASTM D1238
Melt Flow Rate, 360°C/2.16 kgf	22	g/10 min	ASTM D1238
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-104394172	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5 – 1.6	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.