

Product Information

TRIECO 4D21G15 BK (OCEAN)

PA6/Eco plastic

TRIECO 4D21G15 BK (OCEAN)
contains a minimum of 18% ocean plastic.



TYPICAL DATA OF TRIECO 4D21G15 BK (OCEAN)

PROPERTY	UNIT	METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	ISO 1183	1.23
MECHANICAL			
Tensile Strength at yield	MPa	ISO 527	120
Tensile Elongation at break	%	ISO 527	5.5
Flexural Strength at yield	MPa	ISO 178	185
Flexural Modulus	MPa	ISO 178	>5300
Izod Impact Strength, notched, 23°C (1/8")	kJ/m ²	ISO 180	>6.5
THERMAL			
HDT, 18.6 kg _f /cm ²	°C	ISO 75	195
OTHERS			
Mold Shrinkage	%	ASTM D955	<0.2
Long term Heat Stability	Retention%	-	
140°C 1000H, tensile strength	%	-	91%

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE FOR TRIECO 4D21G15 BK (OCEAN)

- General processing conditions for TRIECO 4D21G15 BK(OCEAN) are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	°C	100~120
Drying Time	hr	3 ~ 5
Moisture Content, Max	%	0.02
Melt Temperature	°C	260 ~ 280
Nozzle Temperature	°C	260 ~ 280
Front Temperature	°C	260 ~ 280
Middle Temperature	°C	260 ~ 280
Rear Temperature	°C	265 ~ 285
Mold Temperature	°C	60 ~ 80
Back Pressure	%	< 70
Screw Speed	%	< 60
Injection Pressure	%	< 70
Injection Speed	%	< 50
Hold Pressure	%	< 50
Injection Cushion	Mm	3 ~ 6

SAMYANG Corporation

<http://www.samyang.com>

HEAD OFFICE

Samyang Corporation
31, Jongno 33-gil, Jongno-gu, Seoul, Korea
TEL 82-2-740-7761 FAX 82-2-740-7700

R&D CENTER

Daedeokdae-ro 730, Yuseong-gu, Daejeon, Korea
TEL 82-42-865-8073 FAX 82-42-865-8099

JEONJU PLANT

Palbok-ro 147, Deokjin-gu, Jeonju, Korea
TEL 82-63-210-6660 FAX 82-63-210-6677

SAMYANG KASEI

Ongoeul-ro 376, Deokjin-gu, Jeonju, Korea
TEL 82-63-210-1114 FAX 82-63-211-1240

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

131, Shuangying-Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
TEL 86-21-6922-2270 FAX 86-21-6922-2271

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H-5100, Jászberény, Necső telep 1., Hungary
TEL 36-21-311-1255 FAX 36-21-311-1252