

PRODUCT DATA SHEET


sasol

HDPE	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE	HDPE
High Density Polyethylene HD4985 LS					Technical support: Sasol Chemicals North America LLC 12120 Wickchester Lane Houston, TX 77079 Email: PolymersTechnical@us.sasol.com			Sales office: Sasol Chemicals North America LLC 12120 Wickchester Lane Houston, TX 77079 Telephone: (281) 588 3000 Email: PolymersSales@us.sasol.com	

Date of issue July 17, 2019

www.sasol.com
High Load Melt Index: 8.0 g/10min
Density: 0.949 g/cm³

Features

- Natural bimodal HDPE copolymer
- Good melt strength for a range of pipe wall thicknesses
- Certified to NSF/ANSI Standard 14 - Plastics Piping Components and Related Materials and Certified to NSF/ANSI Standard 61 – Drinking Water System Components – Health Effects
- Product is listed in PPI TR-4 as a PE4710 and a PE100 resin when blended with an approved black master batch

Potential Applications

- Pressure pipe for potable water, natural gas, industrial and mining
- Large diameter pressure pipe with thick walls (typically, >3.5" depending on extrusion conditions and equipment)

Additives

- Designed for the pipe extrusion process and the requirements of pressure pipe system standards

Typical properties (not to be construed as specifications)		Value (English)	Value (SI)	Method
Resin Properties	High Load Melt Index (190°C/21.6kg)	8.0 g/10min	8.0 g/10min	ASTM D1238
	Density	0.949 g/cm ³	0.949 g/cm ³	ASTM D4883
Physical Properties	Tensile Strength at Yield (2 in/min; 50 mm/min)	3500 psi	24.1 MPa	ASTM D638
	Elongation at Yield (2 in/min; 50 mm/min)	10.4%	10.4%	ASTM D638
	Tensile Strength at Break (2 in/min; 50 mm/min)	4400 psi	30.3 MPa	ASTM D638
	Elongation at Break (2 in/min; 50 mm/min)	>600%	>600%	ASTM D638
	Flexural Modulus (2% Secant)	130,000 psi	900 MPa	ASTM D790A
	Izod Notched Impact Strength (73°F / 23°C)	12 ft-lbf/in	63 kJ/m ²	ASTM D256
	Shore D Hardness	64	64	ASTM D2240
Thermal Properties	Vicat Softening Temperature	259°F	126°C	ASTM D1525
	Brittleness Temperature	<-180°F	<-118°C	ASTM D746
	Oxidative Induction Time @ 210°C	>20 min	>20 min	ASTM D3895
	Thermal Stability	>464°F	>240°C	ASTM D3350
Other Properties	ESCR (Condition C: 100% Igepal® F50)	>5000 hrs.	>5000 hrs.	ASTM D1693
	Hydrostatic Design Basis @ 23°C	1600 psi	11.0 MPa	ASTM D2837
	Hydrostatic Design Basis @ 60°C	1000 psi	6.9 MPa	ASTM D2837
	Minimum Required Strength (MRS)	1450 psi	10.0 MPa	ISO 9080 / 12162
	PENT (Notched Tensile)	>10,000 hrs.	>10,000 hrs.	ASTM F1473
	Cell Classification (when blended with approved black masterbatch)	445574C CC3	445576C CC3	ASTM D3350

PRODUCT DATA SHEET



HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE HDPE

Typical Processing Conditions

Specific recommendations for processing of HD4985 LS can only be made when the actual processing equipment and end use application is known. For further information, please contact your Sasol Sales Representative or Technical Specialist. Recommended melt temperature range: 380-440°F (190-230°C)

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours.

Storage

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage.

Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

1. be equipped with adequate filters
2. is operated and maintained in such a manner to ensure no leaks develop
3. that adequate grounding exists at all times

We further recommend that good housekeeping be practiced throughout the facility.

This publication contains information provided in good faith and is indicative, based on Sasol's current knowledge on the subject. No guarantee or warranty is intended or implied. We reserve the right to make changes as a result of technological progress or development. Any information, including suggestions for use of products, should not preclude experimental testing and verification, to ensure the suitability of a product for each specific application. Users must also abide by local and international laws and obtain all necessary permits when required to do so. Prior to handling a hazardous product, consult its safety data sheet. In case of questions or queries, please contact Sasol through our customer service channels. All products purchased from Sasol Chemicals are subject to the terms and conditions as set out in the contract, order confirmation and/or bill of lading.