

PRODUCT DATA SHEET



PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC	PVC
Polyvinyl Chloride S6721							Technical support: Polymer Technology Services Centre 22 Pressburg Road, Modderfontein, 1645 South Africa Tel: +27 (0)11 458 0700 Fax: +27 (0)11 458 0734				Sales office: Sasol Place PO Box 5486 Johannesburg, 2000 South Africa Tel: +27 (0)10 344 5251 Email: polymers@Sasol.com				

Date of issue: January 2018

www.sasol.com
K-value: 67
Apparent Density: 560 g/L

Features

- Homopolymer suspension resin
- Medium molecular weight
- High bulk density
- Medium porosity
- Good processability

Applications

- Extruded pipe and conduit
- Rigid profiles
- Flexible footwear

Additives

- The resin is additive free and need to be blended with an appropriate additive formulation before being processed

Typical properties (not to be construed as specifications)		Value	Unit	Test Method
Physical Properties	K-value	67	-	ISO 1628-2
	Apparent density	560	g/L	ISO 60
	Particle size > 250 µm	< 2.5	%	ISO 4610
	Cold plasticiser absorption	23	%	ISO 4608
	Volatile matter	< 0.3	%	ISO 1269
The data reflected in this table has been obtained from laboratory tests conducted on representative samples of the Sasol PVC S6721 resin. These values are for general guidance only and more detailed information may be obtained by contacting the relevant Account Manager / Technical Specialist.				

PRODUCT DATA SHEET

PVC PVC PVC PVC PVC PVC PVC PVC PVC PVC PVC PVC PVC PVC

Handling

Workers should be protected from the possibility of skin or eye contact with PVC resin containing powders or molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be adequately ventilated to carry away fumes or vapours. Please consult the material safety data sheet (MSDS) for more detailed information.

Storage

As ultraviolet light may cause a change in material properties, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, PVC resins are expected to maintain their original material and processing properties for at least 12 months.

Combustibility

Polyvinyl Chloride resins or compounds will burn when supplied with adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, PVC resins or compounds contribute high heat and generate a dense acidic white smoke. Fires can be extinguished by conventional means with water, water mist being preferred. In enclosed areas, fire fighters should be provided with self-contained breathing apparatus

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all PVC resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

Regulatory & Legal Compliance

Sasol PVC S6721 suspension resin contains less than 1mg/kg (1ppm) residual vinyl chloride. However it remains the responsibility of the manufacturer of the final article to conduct relevant tests on their product to assure appropriate migration requirements are satisfied.

This publication contains information provided in good faith and is indicative, based on Sasol's current knowledge on the subject. No guarantee or warranty is intended or implied. We reserve the right to make changes as a result of technological progress or development. Any information, including suggestions for use of products, should not preclude experimental testing and verification, to ensure the suitability of a product for each specific application. Users must also abide by local and international laws and obtain all necessary permits when required to do so. Prior to handling a hazardous product, consult its safety data sheet. In case of questions or queries, please contact Sasol through our customer service channels. All products purchased from Sasol Chemicals are subject to the terms and conditions as set out in the contract, order confirmation and/or bill of lading.