



Arak Petrochemical Company



ISO 9001:2000
Certificate No.: CH98/8032

ISO 14001:2004
Certificate No.: CH03/0112

OHSAS 18001:1999
Certificate No.: CH05/0675

Address:

No. 3, Taban St.
Vali-e-Asr Ave.
Tehran - IRAN

Tel:

(+98 21)82122700

Fax:

(+98 21)8867 4126-27

Web-site:

www.arpc.ir

E-mail:

Sales@arpc-ir.net

Polypropylene

Moplen EP2X30F

Typical properties	Test method (ASTM)	Unit	Value
MFR @230°C, 2.16 kg	D1238/L	gr/10min	8
Flexural Modulus	D790	Mpa	900
Notched Izod Impact@23°C	D256	J/m	60
Tensile Strength@Yield	D638	Mpa	26
Elongation@Yield	D638	%	12
Vicat Softening Point, 10N	D1525	°C	130
HDT(0.46N/mm ²)	D648	°C	70
Rockwell Hardness	D785	R.Scale	81
Oven Aging@150°C	D3012	Hours	-

➤ Values shown are averages & are not to be considered as product specifications.

❖ Main application & Characteristics:

Moplen EP2X30F is a normally modified polypropylene random copolymer for the production of cast and water-quenched blown film.

Moplen EP2X30F is designed for quality packaging applications, either as monolayer film or as welding layer on co-extruded structures. The product offers excellent process ability, high clarity and gloss and good heat weld ability. The seal initiation temperature is about 136°C.

Moplen EP2X30F is well suited for lamination to bioriented polypropylene film or other materials to form the welding layer.

Film produced with Moplen EP2X30F is particularly suited for the packaging of foodstuffs such as sweets, pasta, biscuits and snacks and for the packaging of books, stationery, shirts and hosiery.

Moplen EP2X30F is furthermore suitable for injection moulding caps and closures.

* Moplen EP2X30F is suitable for food contact.