



Arak Petrochemical Company



ISO 9001:2000
Certificate No.: CH98/8032

ISO 14001:2004
Certificate No.: CH03/0112

OHSAS 18001:1999
Certificate No.: CH05/0675

Address:

No. 3, Taban St.
Vali-e-Asr Ave.
Tehran - IRAN

Tel:

(+98 21)82122700

Fax:

(+98 21)8867 4126-27

Web-site:

www.arpc.ir

E-mail:

Sales@arpc-ir.net

Polypropylene

Moplen HP554P (Fibre)

Typical properties	Test method (ASTM)	Unit	Value
MFR @230°C, 2.16 kg	D1238/L	gr/10min	18
Flexural Modulus	D790	Mpa	1550
Notched Izod Impact@23°C	D256	J/m	30
Tensile Strength@Yield	D638	Mpa	33
Elongation@Yield	D638	%	12
Vicat Softening Point, 10N	D1525	°C	154
HDT(0.46N/mm ²)	D648	°C	95
Rockwell Hardness	D785	R.Scale	102
Oven Aging@150°C	D3012	Hours	120

➤ Values shown are averages & are not to be considered as product specifications.

❖ Main application & Characteristics:

Moplen HP554P is a homo-polymer, suitable for extrusion applications. It is formulated with an anti-gas fading stabilization package.

Moplen HP554P is designed for production of fine denier staple fibres. Typical applications are thermal-bonded non-woven fabrics, upholstery and hygiene, in SSL and some LSL. Diapers, incontinence pads, feminine care, wipe filters.

* Moplen HP554P is suitable for food contact.