



Plastics and Resins

[back to list](#)

Product Name:	Polypropylene Resin (M3700C)					
Trade Mark:	Sanren Brand					
Alternative Name:						
Molecular formula/Structural Formula:	□					
Production Process:	Liquid phase bulk polymerization process is used for production of the product. The polymer produced is of homo-polypropylene type.					
Properties:	The pellet product is colourless and in the shape of a cylinder with satisfied light transmittance and controllable theological property, and anti-static performance, good mechanical properties as well as farly good heat resistance.					
Grade:						
National Standard Grade:	PPH—MZ—425					
Enterprise Standard Grade:	M3700C					
Specifications:	Q/SH 012.07.06-1999 Polypropylene resin					
	No.	Item	Unit	Quality Criteria		
				Premium-grade	1st-grade	On-spec.
						Testing Method
	1	Cleanliness	piece/kg ≤	0—5	6—10	11—20
	2	Melt flow rate	g/10min	37(+6.0)	37(+9.5)	37(+13.0)
	3	Tensile yield strength	MPa ≥	32.0	18.0	15.0
	4	Outrigger Impact strength(23ℓ)	J/m ≥	22.0	18.0	15.5
	5	Vicat softening point	≥	151	143	135
	6	Rockwell hardness	R scale	95	76	66
	7	Yellowness index	≤	4	4	4
						MA 19037
Scope of Application:	Mainly for manufacture of food grade small injection mouldings.					
Major Applications:						
Process Method:	Injection moulding.					
Packing:	Heavy duty PE film bag as inner packaging and PP woven bag as outer packaging. Each bag has a net weight of 25kg.					
Packing Size:						
Storage:	The product should be stored in a dry, well ventilated warehouse. To avoid direct sunlight, the product should not be stored in the open air.					
Transportation:	By means of truck, vessel or train. During transportation, the product should not be exposed to the sunlight and rain. Neither should the product be mixed with contaminants. There should be no heavy bump or unloading by throwing the bags					
Safety Precautions:	1.Be away from fire and heat sources. 2.Should not be stored or transported together with chemicals and inflammables. 3.Warehouse must be equipped with extinguishers or fire fighting device. 4.Water, carbon dioxide, dry powder or 1211 can be used as extinguishers for the product.					

