



شركة الصحراء العالمية للبتروكيماويات
(شركة مساهمة سعودية)

Sahara International Petrochemical Company
(Saudi Joint Stock Company)

Technical Data Sheet

Sahara H 250 FF

Polypropylene, Homopolymer

Sahara H 250 FF is a homopolymer suitable for extrusion applications. This grade is formulated with anti-gas fading stabilization package. Sahara H 250 FF is used for production of continuous filaments (CF), Bulk continuous filaments (BCF) and staple fibers.

Typical applications are carpet, upholstery, ropes etc.

Product Characteristics:

Status	:	Commercial:Active
Applications	:	Bulk Continuous Filament & Continuous Filament; Filament Yarn
Attribute	:	Gas-fading Resistant
Processing Method	:	Continuous Filament/Spinning; Staple Fiber
Market	:	Textile

Typical Properties	Method	Nominal Value	Unit
Physical			
Melt flow rate (MFR) (230°C/2.16kg)	ISO1133 - 1	25	g/10 min
Melt volume flow rate (230°C/2.16kg)	ISO1133 - 1	34	cm ³ /10min
Mechanical			
Flexural Modulus	ISO 178	1350	Mpa
Tensile Stress at Yield	ISO 527-1, -2	32	Mpa
Tensile Strain at Yield	ISO 527-1, -2	10	%
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	97	°C
Vicat softening temperature (A/50N)	ISO 306	153	°C

• C.R. 2055007570
• P.O. Box 12021 | Jubail Industrial City 31961 | Kingdom of Saudi Arabia
• T +966 13 359 9999 | F +966 13 359 9610
• Capital: SR 7,333,333,320

• س.ت. ٢٠٥٥٠٧٥٧٠
• ص.ب. ١٢٠٢١ | مدينة الجبيل الصناعية ٣١٩٦١ | المملكة العربية السعودية
• هاتف +٩٦٦ ١٣ ٣٥٩ ٩٩٩٩ | فاكس +٩٦٦ ١٣ ٣٥٩ ٩٦١٠
• رأس المال ٧,٣٣٣,٣٣٣,٣٢٠ ريال سعودي



شركة الصحراء العالمية للبتروكيماويات
(شركة مساهمة سعودية)

Sahara International Petrochemical Company
(Saudi Joint Stock Company)

Notes:

Typical properties; not to be construed as specifications.

Users should review the applicable Material Safety Data Sheet before handling the product.

Before using a product sold Sahara Marketing Company, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; express or implied (including any warranty of merchantability or fitness for a particular purpose or any warranty) other than as separately agreed to by the parties in a contract.

This product(s) may not be used in:

- any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I medical devices, without prior notification to Seller for each specific product and application; or
- the manufacture of any of the following, without prior written approval by Seller for each specific product and application: U.S. FDA Class II Medical Devices; Health Canada Class II or Class III Medical Devices; European Union Class II Medical Devices; film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; and tobacco related products and applications.

Additionally, the product(s) may not be used in:

- U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices;
- applications involving permanent implantation into the body;
- life-sustaining medical applications; and (iv) lead, asbestos or MTBE related applications. All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Processing Techniques:

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Health and Safety:

The resin is manufactured to the highest standards, but special requirements apply to certain applications such as food end-use contact and direct medical use. For specific information on regulatory compliance contact your local representative.

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may be degraded if it is exposed to air during any of the processing and off- line operations. The products of degradation may have an unpleasant odor. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes or vapours. Legislation on the control of emissions and pollution prevention should be observed.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. While burning, the resin contributes high heat and may generate a dense black smoke.

Recycled resins may have previously been used as packaging for, or may have otherwise been in contact with, hazardous goods. Converters are responsible for taking all necessary precautions to ensure that recycled resins are safe for continued use.

For further information about safety in handling and processing please refer to the Safety Data Sheet.



شركة الصحراء العالمية للبتروكيماويات
(شركة مساهمة سعودية)
Sahara International Petrochemical Company
(Saudi Joint Stock Company)

Conveying:

Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks

Storage:

The resin is packed in 25 kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i. e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavorable storage conditions may also intensify the resin's slight characteristic odor.

Resin should be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the material on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

Compliance & Product Stewardship Department

Contact Details:

Website: www.sipchem.com
Email: marketing@sipchem.com
Phone: +966 13 359 3372

Disclaimer

Before using the product listed above, customers and other users should take care in determining the suitability of such product for the intended use. SIPCHEM do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.

• C.R. 2055007570
• P.O. Box 12021 | Jubail Industrial City 31961 | Kingdom of Saudi Arabia
• T +966 13 359 9999 | F +966 13 359 9610
• Capital: SR 7,333,333,320

• س.ت. ٢٠٥٥٠٧٥٧٠
• ص.ب. ١٢٠٢١ | مدينة الجبيل الصناعية ٣١٩٦١ | المملكة العربية السعودية
• هاتف ٩٦٦ ١٣ ٣٥٩ ٩٩٩٩ | فاكس ٩٦٦ ١٣ ٣٥٩ ٩٦١٠
• رأس المال ٧,٣٣٣,٣٣٣,٣٢٠ ريال سعودي