



Sahara C 700HT

Polypropylene, Impact Copolymer

TECHNICAL DATA SHEET

Description

SAHARA C 700HT is a nucleated impact copolymer used for injection molding and compounding applications. It exhibits good impact to stiffness balance combined with high fluidity. Sahara C 700 HTX is typically used in opaque containers, housewares, toys and in thin wall containers for food packaging (e.g. Margarine tubs, Yoghurt pots) and compounding applications.

Product Characteristics

Commercial: Active.

Processing Method: Injection Molding.

Typical applications: Thin wall containers; housewares.

Typical Properties	Test Method	Nominal Value	Unit
Physical			
Density	ISO1183-1	0.90	g/cm ³
Melt Flow Rate 230 °C/2.16 kg.	ISO1133	70	g/10 min
Mechanical			
Flexural Modulus	ISO 178	1545	MPa
Tensile Modulus	ISO 527-1, -2	1540	MPa
Tensile Stress at Yield	ISO 527-1, -2	24	MPa
Tensile Strain at Yield	ISO 527-1, -2	4	%
Charpy Impact Notched, Type 1, Edgewise, Notch A, 23 °C	ISO 179	5.10	kJ/m ²
Charpy Impact Notched, Type 1, Edgewise, Notch A, 0 °C	ISO 179	3.80	kJ/m ²
Charpy Impact Notched, Type 1, Edgewise, Notch A, -20 °C	ISO 179	3.00	kJ/m ²
Notched Izod Impact Strength, 23 °C	ISO 180	4.20	kJ/m ²
Thermal			
Heat Deflection Temperature-A, 1.8 MPa, unannealed	ISO 75B-1, -2	60	°C
Heat Deflection Temperature -B, 0.45 MPa, unannealed	ISO 75B-1, -2	101	°C
Vicat Softening Temperature, A50	ISO 306	147	°C
Vicat Softening Temperature, B50	ISO 306	71	°C

Processing Condition

Barrel temperature range: 210 -250 °C

Mold temperature: 15 -40 °C

Melt temperature: 240 -260 °C

Mold Shrinkage: 1 – 2.5 %

Revision Sep 2022

EXCELLENCE everywhere



Sahara C 700HT

Polypropylene, Impact Copolymer

Safety and Handling

The product is not classified as a hazardous material. Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. Sipchem would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery. Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks. For additional information about safety, handling and storage. Safety Data Sheets (SDS) are available on our website.

Food Contact Regulation

This product complies with the relevant requirements of EU, China, South America & United States Food contact. Declaration of Compliance Certificate are available on our Internet site. For additional specific information please contact Product Stewardship team

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

Contacts

Sales and Marketing Company

E marketing@sipchem.com

Compliance & Product Stewardship

E compliance@sipchem.com

Sipchem Company

W www.sipchem.com