

Technical Information

Smart™ 183

Introduction

Smart™ 183, metallocene LLDPE, is an **ethylene-octene copolymer** produced via Nexlene™ technology. Smart™ 183 performs well in a wide range of general purpose LLDPE cast film applications.

Typical Performance:

- High stiffness and toughness
- Superior processability and neck-in phenomenon

Compiles with:

- US. FDA 21 CFR 177.1520
- EU. No 10/2011

Additives:

- Antiblock: No
- Slip: No

Properties

		Typical Values	Unit	Test Method
Resin Properties	Density	0.918	g/cm ³	ASTM D792
	Melt index (2.16 kg @190°C)	3.0	g/10min	ASTM D1238
	Melting temperature	115	°C	SK Method
	Vicat softening temperature	105	°C	ASTM D1525
Film Properties	Film thickness – tested	25	µm	ASTM D374
	Dart impact strength	270	g	ASTM D1709A
	Haze	1.5	%	ASTM D1003
	Seal initiation temperature	105	°C	SK Method ¹
	Elmendorf tear strength	MD 10	g/µm	ASTM D1922
		TD 21	g/µm	ASTM D1922
	Tensile strength at break	MD 500	kg/cm ²	ASTM D882
		TD 400	kg/cm ²	ASTM D882

Technical Information

Elongation at break	MD	450	%	ASTM D882
	TD	700	%	ASTM D882
Secant modulus (1%)	MD	1140	kg/cm ²	ASTM D882
	TD	1350	kg/cm ²	ASTM D882

Extrusion Condition	•	Screw size: 30 mm
	•	Screw speed: 30 rpm
	•	Die gap: 1 mm
	•	Melt temperature: 230°C

¹ Temperature at which 0.4 kg/25.4 mm heat seal strength is achieved

Notes

These are **typical values** and are **not be construed as specifications**. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK Global Chemical Co.,LTD
26 Jong-ro, Jongno-gu,
Seoul, Korea
TEL +82-2-2121-5052

TS&D SK innovation Global Technology
325 Exporo, Yueseong-gu,
Daejeon, Korea
TEL +82-42-609-8623

Revised: Aug. 5th, 2016

Copyright SK