

Product Data Sheet

SUPRENE[®] 501A



Product Data Sheet

Date Prepared: July 3, 2018

SUPRENE[®] 501A

SUPRENE EPDM 501A is a low Mooney Viscosity and ENB type grade.

It shows excellent mill processability.

It has good flow and is suitable for molding complicated shaped products.

It is also suitable for extrusion of cable.

Main uses of SUPRENE EPDM 501A are found in gasket, roll, electric parts, wire & cable, various rubber coated fabrics and general industrial parts.

Raw Polymer Properties

	Test Method	Unit	Min.	Max.	Typical Value
Mooney Viscosity, (ML 1+4, 100 °C unmilled)	ASTM D1646	-	41	51	46
Ethylene Content *	ASTM D3900	wt%	50	56	53
ENB Content	ASTM D6047	wt%	3.1	5.1	4.1
Oil Content	-	phr	-	-	-
Specific Gravity	ASTM D792	-	-	-	0.86
Volatile Matter	ASTM D5668	wt%	-	0.8	0.2
Ash	ASTM D5667	wt%	-	0.15	0.01
Physical Form, (kg/bale)	-	-	-	-	25kg (Dense Bale)

* Ethylene Content + Propylene Content = 100%

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



SUPRENE[®] 501A

Typical Properties

Properties	Test Method	S501A
Mooney Viscosity ML 1+4 @ 125°C	ASTM D1646	30.0
Ethylene Content, wt%	ASTM D3900	53.0
ENB Content, wt%	ASTM D6047	4.1

Guide Formulation

Formulation 1

	S501A
S501A	100
HAF	50
ZnO	5.0
Stearic Acid	1.0
TMTM(TS)	1.0
MBT(M)	0.3
Sulfur	1.0
Total	158.3

* Unit: phr

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



Properties	Test Method	S501A
Compound Mooney Viscosity ML 1+4 @ 100°C	ASTM D1646	78.9
Pre-vulcanization characteristics Large Rotor at 125°C	ASTM D1646	
Minimum Viscosity (Vm)		48.5
t'5 (min)		19.15
t'35 (min)		30.33
Δt30		11.18
Rotorless Cure Meter (MDR, 160°C/30min)	ASTM D5289	
M _L (lb·in)		2.93
M _H (lb·in)		26.13
t _{s2} (min)		2.94
t _{c50} (min)		4.97
t _{c90} (min)		8.46

Cured at 160°C for 10 min

Properties	Test Method	S501A
Specific Gravity	ASTM D792	1.07
Hardness (shore A)	ASTM D2240	74
Tensile Strength (kgf/cm ²)	ASTM D412	205
Elongation (%)	ASTM D412	501
100% Modulus (kgf/cm ²)	ASTM D412	35.5

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



Formulation 2

	S501A
S501A	100
FEF	60
MB	1.5
ZnO	5.0
Stearic Acid	0.5
TAIC	1.0
DCP	8.0
Total	176.0

* Unit: phr

Properties	Test Method	S501A
Compound Mooney Viscosity ML 1+4 @ 100°C	ASTM D1646	101.5
Pre-vulcanization characteristics	ASTM D1646	
Large Rotor at 125°C		
Minimum Viscosity (Vm)		50.6
t'5 (min)		5.63
t'35 (min)		8.50
Δt30		2.87
Rotorless Cure Meter (MDR, 160°C/30min)	ASTM D5289	
M _L (lb·in)		2.94
M _H (lb·in)		88.64
t _{S2} (min)		0.50
t _{C50} (min)		5.00
t _{C90} (min)		17.81

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



Cured at 160 °C for 20 min

Properties	Test Method	S501A
Specific Gravity	ASTM D792	1.09
Hardness (shore A)	ASTM D2240	81
Tensile Strength (kgf/cm ²)	ASTM D412	135
Elongation (%)	ASTM D412	82
100% Modulus (kgf/cm ²)	ASTM D412	-

Heat Resistance

Properties	Test Method	S501A
Hardness (Change Point)	ASTM D2240	+3
Tensile Strength (Change %)	ASTM D412	-50
Elongation (Change %)	ASTM D412	-40

** After 72 hours oven aging at 150 °C per ASTM D573*

Compression Set

Properties	Test Method	S501A
Compression Set (%)	ASTM D395 (Method B)	10.3

** After 48 hours at 150 °C*

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.

The **Innovative Chemical** Company

The global chemical company that never stops its transformation to build the best-ever chemical portfolio.
SK global chemical creates the new future of the chemical industry toward its customers and markets.

The general energy and chemical leader in the global market,
SK global chemical



SK global chemical Co., Ltd. 26, Jong-ro, Jongno-gu, Seoul, Korea

TEL +82-2-2121-5114 FAX +82-2-2121-7001

© 2016 SK global chemical Co., Ltd