

Product Data Sheet

SUPRENE[®] 503



Product Data Sheet

Date Prepared: July 5, 2018

SUPRENE® 503

SUPRENE EPDM 503 is ENB type grade, which has high ethylene content and low Mooney Viscosity.

It shows excellent mechanical properties even in high hardness compound.

It has good flow property and is suitable for weather strip with high hardness and low compression set.

Main uses of SUPRENE EPDM 503 are found in weather strip, joint, molded parts, electric parts, wire & cable, various rubber coated materials and general industrial parts.

Raw Polymer Properties

	Test Method	Unit	Min.	Max.	Typical Value
Mooney Viscosity, (ML 1+4, 100 °C unmilled)	ASTM D1646	-	32	40	36
Ethylene Content *	ASTM D3900	wt%	69	73	71
ENB Content	ASTM D6047	wt%	5.2	6.2	5.7
Oil Content	-	phr	-	-	-
Specific Gravity	ASTM D792	-	-	-	0.86
Volatile Matter	ASTM D5668	wt%	-	0.8	0.3
Ash	ASTM D5667	wt%	-	0.15	0.01
Physical Form, (kg/bale)	-	-	-	-	25kg (Dense Bale)

* Ethylene Content + Propylene Content = 100%

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



SUPRENE® 503

Typical Properties

Properties	Test Method	S503
Mooney Viscosity ML 1+4 @ 100°C	ASTM D1646	38.0
Ethylene Content, wt%	ASTM D3900	71.0
ENB Content, wt%	ASTM D6047	5.7

Guide Formulation

	Formulation 1	Formulation 2
S503	100.0	100.0
HAF	50.0	80.0
P-6	50.0	10.0
ZnO	5.0	5.0
Stearic Acid	1.0	1.0
MBT(M)	0.5	0.5
TMTD(TT)	1.0	1.0
Sulfur	1.5	1.5
Total	209.0	199.0

* Unit: phr

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



Properties	Test Method	Formulation 1	Formulation 2
Compound Mooney Viscosity ML 1+4 @ 100°C	ASTM D1646	18.2	73.6
Pre-vulcanization characteristics Large Rotor at 125°C	ASTM D1646		
Minimum Viscosity (Vm)		11.0	78.3
t'5 (min)		22.82	9.90
t'35 (min)		45.22	15.48
Δt30		22.30	5.58
Rotorless Cure Meter (MDR, 160°C/30min)	ASTM D5289		
M _L (lb·in)		0.62	5.03
M _H (lb·in)		18.60	50.99
ts2 (min)		2.84	1.14
tc50 (min)		4.74	2.81
tc90 (min)		10.1	8.11

Cured at 160°C for 20 min

Properties	Test Method	Formulation 1	Formulation 2
Specific Gravity	ASTM D792	1.03	1.14
Hardness (shore A)	ASTM D2240	63	86
Tensile Strength (kgf/cm ²)	ASTM D412	121	192
Elongation (%)	ASTM D412	398	202
100% Modulus (kgf/cm ²)	ASTM D412	22.1	120.7

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



Heat Resistance

Properties	Test Method	Formulation 1	Formulation 2
Hardness (Change Point)	ASTM D2240	+2	+1
Tensile Strength (Change %)	ASTM D412	-32	+21
Elongation (Change %)	ASTM D412	-39	-27

* After 72 hours oven aging at 120 °C per ASTM D573

Compression Set

Properties	Test Method	Formulation 1	Formulation 2
Compression Set (%)	ASTM D395 (Method B)	21.4	13.4

* After 72 hours at 70 °C

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.

The **Innovative Chemical** Company

The global chemical company that never stops its transformation to build the best-ever chemical portfolio.
SK global chemical creates the new future of the chemical industry toward its customers and markets.

The general energy and chemical leader in the global market,
SK global chemical



SK global chemical Co., Ltd. 26, Jong-ro, Jongno-gu, Seoul, Korea

TEL +82-2-2121-5114 FAX +82-2-2121-7001

© 2018 SK global chemical Co., Ltd