

Product Data Sheet

SUPRENE[®] 7486F



Product Data Sheet
Date Prepared: July 6, 2018

SUPRENE[®] 7486F

SUPRENE EPDM 7486F is a non-oil extended grade with very high Mooney viscosity and extra high ENB content.

SUPRENE EPDM 7486F shows excellent extrusion processability due to its tailored molecular architecture and its moderate ethylene content gives a better flexibility under low temperature condition, compared with high ethylene grades. Especially, controlled cellular structure with dimensional stability can be realized with fast curing performance with this high ENB grade.

SUPRENE EPDM 7486F is suitable for sponge application made by continuous vulcanization such as window seal, body seal for automotive and adiabatic sponge.

Raw Polymer Properties

	Test Method	Unit	Min.	Max.	Typical Value
Mooney Viscosity, (ML 1+4, 150 °C unmilled)	ASTM D1646	-	63	71	67
Ethylene Content *	ASTM D3900	wt%	58	62	60
ENB Content	ASTM D6047	wt%	8.0	10.0	9.0
Specific Gravity	ASTM D792	-	-	-	0.86
Volatile Matter	ASTM D5668	wt%	-	0.8	-
Ash	ASTM D5667	wt%	-	0.15	-
Physical Form, (kg/bale)	-	-	-	-	Friable Bale (25 kg/bale)

* Ethylene Content + Propylene Content = 100%

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



SUPRENE[®] 7486F

Typical Properties

Properties	Test Method	S7486F
Mooney Viscosity ML 1+4 @ 150°C	ASTM D1646	67.0
Ethylene Content, wt%	ASTM D3900	60.0
ENB Content, wt%	ASTM D6047	9.0

Guide Formulation

	S7486F
S7486F	100.0
GPF (N660)	90.0
CaCO ₃	30.0
P-6 Oil	76.0
ZnO	5.0
Stearic Acid	1.0
MBT(M)	1.5
TMTD(TT)	1.0
ZnBDC(BZ)	1.5
Sulfur	1.5
B.A OBSH	2.0
AC 330	1.0
Total	310.5

* Unit: phr

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



Properties	Test Method	S7486F
Compound Mooney Viscosity ML 1+4 @ 100°C	ASTM D1646	44.0
Pre-vulcanization characteristics Large Rotor at 125°C	ASTM D1646	
Minimum Viscosity (Vm)		27.7
t'5 (min)		8.25
t'35 (min)		11.82
Δt30		3.57
Rotorless Cure Meter (MDR, 160°C/30min)	ASTM D5289	
M _L (lb·in)		1.5
M _H (lb·in)		19.9
t _{s2} (min)		0.87
t _{c50} (min)		2.40
t _{c90} (min)		13.04

Cured at 160°C for 20 min

Properties	Test Method	S7486F
Specific Gravity	ASTM D792	1.16
Hardness (shore A)	ASTM D2240	64
Tensile Strength (kgf/cm ²)	ASTM D412	123
Elongation (%)	ASTM D412	373
100% Modulus (kgf/cm ²)	ASTM D412	30.9

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.



Heat Resistance

Properties	Test Method	S7486F
Hardness (Change Point)	ASTM D2240	+5
Tensile Strength (Change %)	ASTM D412	-9
Elongation (Change %)	ASTM D412	-35

* After 72 hours oven aging at 120 °C per ASTM D573

Compression Set

Properties	Test Method	S7486F
Compression Set (%)	ASTM D395 (Method B)	
After 72 hours at 100°C		38.7

Foam Extrusion

Properties	Test Method	S7486F
Specific Gravity	ASTM D792	0.51
Average Cell Size (µm)	-	95.7
Compression Set (%)	ASTM D395 (Method B)	
After 72 hours at 100°C		55.6

* UHF: 250 °C, Microwave 1.0kW, HAV: 180 °C, Line Speed 1.5m/min

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.

The **Innovative Chemical** Company

The global chemical company that never stops its transformation to build the best-ever chemical portfolio.
SK global chemical creates the new future of the chemical industry toward its customers and markets.

The general energy and chemical leader in the global market,
SK global chemical



SK global chemical Co., Ltd. 26, Jong-ro, Jongno-gu, Seoul, Korea

TEL +82-2-2121-5114 FAX +82-2-2121-7001

© 2016 SK global chemical Co., Ltd