



Data Sheet
Date Prepared:

LLDPE FT610

YUCLAIR FT610 is octene-1 and butene-1 copolymer designed for use in stretch wrap and casting type packaging film application. YUCLAIR FT610 provides stronger film than ones made from competitive LLDPE film grades. Therefore YUCLAIR FT610 shows superior tensile strength, tear strength, impact strength, gel-free, cling property.

YUCLAIR FT610 can be processed readily into casting film using standard extrusion techniques. YUCLAIR FT610 complies with FDA regulations in 21 CFR177.1520 for all food contact.

Application / Use Case

Film / industrial, T-Die

Specification

	Specification	Unit	Test Method
Density	0.919	g/cm ³	ASTM D1505
Melt Index	2.1	g/10min	ASTM D1238
Additives	-		SK Method

Physical Properties

	Value	Unit	Test Method
Film Thickness	30	μm	ASTM D746
Softening Point(Vicat)	102	°C	ASTM D1525
Tensile Strength at Yield(MD)	110	kg/cm ²	ASTM D882

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea
Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea
Technology Tel. 82-42-866-7624 Fax. 82-42-866-7603

Online www.skglobalchemical.com
www.skchem.com

ISO 9001 Certified





Tensile Strength at Yield(TD)	110	kg/cm ²	ASTM D882
Tensile Strength at Break(MD)	400	kg/cm ²	ASTM D882
Tensile Strength at Break(TD)	360	kg/cm ²	ASTM D882
Elongation at Break(MD)	700	%	ASTM D882
Elongation at Break(TD)	750	%	ASTM D882
Tear Strength(MD)	10	g/μm	ASTM D1922
Tear Strength(TD)	12	g/μm	ASTM D1922
Brittleness Temperature	< -70	°C	ASTM D746
Elongation	700/750	%	ASTM D638
Spencer Impact Strength	6	kg·cm	ASTM D3420
Haze	2.0	%	ASTM D1003

These are typical properties only, and are not to be construed as specific limits.

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea
 Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of Technology 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea
 Tel. 82-42-866-7624 Fax. 82-42-866-7603

Online www.skglobalchemical.com
www.skchem.com

ISO 9001 Certified

