



Data Sheet
Date Prepared:

LLDPE FT710

YUCLAIR FT710 is octene-1 and butene-1 copolymer designed for use in stretch wrap and casting type packaging film application. YUCLAIR FT710 provides stronger film than ones made from competitive LLDPE film grades. Therefore YUCLAIR FT710 shows superior tensile strength, tear strength, impact strength, gel-free, cling property. YUCLAIR FT710 can be processed readily into casting film using standard extrusion techniques.

Application / Use Case

Film / industrial, T-Die

Specification

	Specification	Unit	Test Method
Density	0.919	g/cm ³	ASTM D1505
Melt Index	2.5	g/10min	ASTM D1238
Additives	-		SK Method

Physical Properties

	Value	Unit	Test Method
Film Thickness	30	μm	ASTM D746
Tensile Strength at Yield(MD)	110	kg/cm ²	ASTM D882
Tensile Strength at Yield(TD)	110	kg/cm ²	ASTM D882
Tensile Strength at Break(MD)	410	kg/cm ²	ASTM D882
Tensile Strength at Break(TD)	360	kg/cm ²	ASTM D882

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea
Tel. 82-2-2121-5114 Fax. 82-2-2121-7001
SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea
Technology Tel. 82-42-866-7624 Fax. 82-42-866-7603
Online SK energy co., ltd. : www.SKenergy.com
Chemical Business : www.skchem.com

ISO 9001 Certified



Elongation at Break(MD)	750	%	ASTM D882
Elongation at Break(TD)	780	%	ASTM D882
Tear Strength(MD)	11	g/μm	ASTM D1922
Tear Strength(TD)	12	g/μm	ASTM D1922
Spencer Impact Strength	6	kg·cm	ASTM D3420
Haze	2.0	%	ASTM D1003

These are typical properties only, and are not to be construed as specific limits.

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea
Tel. 82-2-2121-5114 Fax. 82-2-2121-7001
SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea
Technology Tel. 82-42-866-7624 Fax. 82-42-866-7603
Online SK energy co., ltd. : www.SKenergy.com
Chemical Business : www.skchem.com

ISO 9001 Certified