



Data Sheet  
Date Prepared:

## HDPE MM810

### Application / Use Case

Fiber / Span bond

### Characteristic

Processibility, Adhesive

### Specification

|            | Specification | Unit              | Test Method |
|------------|---------------|-------------------|-------------|
| Density    | 0.954         | g/cm <sup>3</sup> | ASTM D1505  |
| Melt Index | 30            | g/10min           | ASTM D1238  |

### Physical Properties

|                           | Value | Unit               | Test Method |
|---------------------------|-------|--------------------|-------------|
| Tensile Strength at Yield | 250   | kg/cm <sup>2</sup> | ASTM D638   |
| Flexural Modulus          | 9000  | kg/cm <sup>2</sup> | ASTM D790   |

These are typical properties only, and are not to be construed as specific limits.

Head Office  
99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea  
Tel. 82-2-2121-5114 Fax. 82-2-2121-7001  
SK Institute of  
140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea  
Technology  
Tel. 82-42-866-7624 Fax. 82-42-866-7603  
Online  
www.skglobalchemical.com  
www.skchem.com

ISO 9001 Certified

