

ESPOLEX®

THERMOPLASTIC ELASTOMER

WT466

Nominal Physical Properties ⁽¹⁾	ISO Test Method	Unit	WT466
Density	ISO 1183	kg/m ³	880
Melt Flow: Condition 230°C/ 98.07N	ISO 1133	g/10min	15
Surface Hardness	ISO 868	Shore A	85
Tensile Strength			
100% Modulus	ISO 37	MPa	3.9
Breaking Strength	Type 1A	MPa	13.5
Elongation at Break	200mm/min	%	735
Compression Set 70C, 22Hrs	ASTM D395, Method B	%	75

Suggested Applications:

- Profile Extrusions
- Sheet and Hose
- Gaskets and Seals

Note 1: The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes.

February 2009

This document reports accurate and reliable information to the best of our knowledge, but our suggestions and recommendations cannot be guaranteed because the conditions of use are beyond our control. Information presented herein is given without reference to any patent questions which may be encountered in the use thereof. Such questions should be investigated by those using this information. Sumitomo Chemical Co., Ltd. Assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.

	Sumitomo Chemical North America	Sumitomo Chemical Europe	Sumitomo Chemical Asia
	335 Madison Avenue, Suit 830 New York, NY 10017, U.S.A. Tel: + 1-212-572-8200 or + 1-877-377-6539 (toll-free) Fax: + 1-212-572-8234	Woluwelaan 57 B-1830 Machelen, Belgium Tel: + 32-2-251-0650 Fax: + 32-2-251-2991	Tokyo Sumitomo Twin Building 27-1, Shinkawa 2-chome, Chuo-ku Tokyo 104-8260, Japan Tel: + 81-3-5543-5452 Fax: + 81-3-5543-5277

WWW.ESPOLEX.COM