

ESPOLEX®

THERMOPLASTIC ELASTOMER

WT515

Nominal Physical Properties ⁽¹⁾	ASTM Test Method	Unit	WT515
Density	D1505 (JIS K7112)	kg/m ³	880
Melt Flow, Condition 230°C/2.16Kg	D1238 (JIS K7210)	g/10min	7.0
Modulus	D790	MPa	340
Tensile Strength	ASTM D412 500mm/min	MPa	11.0
Tensile Elongation	(Tensile) Dumbbell Die "C"	%	560
Izod Impact Strength			
At -40°C	D256	J/m	No Break
At -45°C		J/m	No Break
Brittle temp	ASTM D746	°C	<-60

Suggested Applications:

- Air Bag Covers
- MIC Applications
- Interior Trim
- Injection Molded Parts

Note: The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes.

April 2009

This document reports accurate and reliable information to the best of our knowledge, but our suggestions and recommendations cannot be guaranteed because the conditions of use are beyond our control. Information presented herein is given without reference to any patent questions which may be encountered in the use thereof. Such questions should be investigated by those using this information. Sumitomo Chemical Co., Ltd. Assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.



Sumitomo Chemical North America

335 Madison Avenue, Suit 830
New York, NY 10017, U.S.A.
Tel: + 1-212-572-8200 or
+ 1-877-377-6539 (toll-free)
Fax: + 1-212-572-8234

Sumitomo Chemical Europe

Woluwelaan 57
B-1830 Machelen, Belgium
Tel: + 32-2-251-0650
Fax: + 32-2-251-2991

Sumitomo Chemical Asia

Tokyo Sumitomo Twin Building
27-1, Shinkawa 2-chome, Chuo-ku
Tokyo 104-8260, Japan
Tel: + 81-3-5543-5452
Fax: + 81-3-5543-5277

WWW.ESPOLEX.COM